

Table 1: Results from four-point bending and torsion tests, showing data from individual specimens and combined treatment means and standard deviations.

<i>Treatment</i>	<i>Bending Stiffness (N/mm)</i>	<i>Ultimate Torque (N·m)</i>	<i>Yield Torque (N·m)</i>	<i>Torsional Rigidity (N·m²/radian)</i>
Scaffold	780	24	16	12
Scaffold	1,400	52	30	31
Mean ± Standard Deviation	1,090 ± 440	38 ± 19	23 ± 10	21 ± 13
Control	1,200	34	24	20
Control	950	15	12	11
Mean ± Standard Deviation	1,070 ± 170	25 ± 14	18 ± 8	15 ± 7