

Predictive Modelling of the Mechanical Strength of Wire Arc Additive Manufactured Metal Parts

Kennedy Osaighe Amedu

`dean.engineering@mudiameuniversity.edu.ng`

Mudiame University, Irrua, Edo State <https://orcid.org/0000-0001-6443-7445>

Paul Kah

University West Department of Engineering Science: Hogskolan Vast Institutionen for
ingenjorsvetenskap

Research Article

Keywords: Wire Arc Additive Manufacturing, Yield Strength, Cooling Rate, Travel Speed, Wire Feed Speed

Posted Date: October 23rd, 2026

DOI: <https://doi.org/10.21203/rs.3.rs-10942509/v1>

License:  This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Predictive Modelling of Wire Arc Additive Manufactured Metal Parts

Kennedy Osaighe Amedu^{*1}, Paul Kah²

1 Department of Mechanical Engineering, Mudiame University, Irrua, Edo State, 310112, Nigeria

2 Department of Engineering Science / Division of Mechanical Engineering, University West, SE-46186 Trollhättan, Sweden

*** Corresponding Author Email: dean.engineering@mudiameuniversity.edu.ng**

Abstract:

Predictive modeling of the mechanical strength of parts produced via Wire Arc Additive Manufacturing (WAAM) is critical for advancing the technology from prototyping to demanding structural applications. Traditional data-driven models often lack accuracy outside their training datasets, creating a need for frameworks that incorporate fundamental physics.

This paper presents a predictive modeling approach that integrates first-principles models to predict the yield strength of WAAM-fabricated components. By modeling the core thermal history, solidification kinetics, and phase transformation mechanisms, the framework establishes a direct link between process parameters such as heat input, travel speed, and cooling rate to the final microstructural evolution.

The first-principles approach offers an analytical-physical framework to simulate the transient temperature fields and subsequent grain growth during multi-layer deposition. This metallurgical data serves as the foundation for a mechanistic strength model based on Hall-Petch grain size strengthening, solid solution hardening, and dislocation density evolution.

Validation will be done against experimental data from WAAM-printed steel specimens. The first principles model demonstrates superior predictive accuracy and generalization capabilities compared to purely empirical methods which use dataset such as those generated from experimental investigation or with a combination with transient thermo-mechanical finite element (FE) simulations.

The findings will provide a robust tool for real-time quality control, process optimization, and the accelerated qualification of high-performance WAAM components as well as a reliable digital twin framework for WAAM.

Keywords: Wire Arc Additive Manufacturing, Yield Strength, Cooling Rate, Travel Speed, Wire Feed Speed

1. Introduction

Wire Arc Additive Manufacturing (WAAM) is a large-scale metal 3D printing technology that melts metal wire feedstock using an electric arc to deposit material layer by layer. Classified under the Directed Energy Deposition (DED) family, WAAM combines standard automated welding technology with robotic or CNC motion systems to construct near-net-shape components without the need for custom moulds, dies, or tooling [1, 10]. WAAM systems rely on three primary electric arc methods as their thermal heat source, each offering its own specific operational tradeoffs.

Gas Metal Arc Welding (GMAW), also known as MIG/MAG uses the wire itself as the melting electrode. It is the most common variant because it utilizes a consumable wire electrode. Because the raw metal wire doubles as the electrode, the welding torch can move in any direction without needing a complex, rotating wire-feed mechanism.

This dramatically simplifies the robotic path planning, yielding high deposition rates [109]. A popular sub-variant is Fronius's Cold Metal Transfer (CMT), which reduces heat input and minimizes spatter [2, 3].




Figure 1 – WAAM-GMAW System [111]

Gas Tungsten Arc Welding (GTAW / TIG) is another welding technology for WAAM which uses a non-consumable tungsten electrode to generate the arc, requiring an external mechanism to feed the wire. This adds robotic programming complexity but offers stable control, making it a preferred choice for materials prone to arc instability like titanium [1, 4].




Figure 2 – WAAM GTAW System [111]

Plasma Arc Welding (PAW) technology is also applied in WAAM. It uses a highly constricted plasma arc that delivers up to three times the energy density of GTAW. It provides exceptionally fast print speeds and minimal welding distortion [1].




Figure 3 – Plasma Arc Welding (PAW) WAAM Process [111]

WAAM offers key advantages when compared to other manufacturing processes. It has high deposition rates as it prints metal exceptionally fast, achieving deposition speeds between 1 to 10 kg/hour. This vastly outperforms slower, powder-bed-based laser systems [1, 5, 6]. Because the process does not require an enclosed vacuum chamber, component size is bounded only by the reach of the robotic arm or gantry system. Systems can manufacture components measuring several meters in scale [1]. WAAM is cost efficient and has high buy-to-fly ratio. Metal wire feedstock is significantly less expensive than specialized atomized metal powders. It achieves near 100% material utilization, lowering raw material waste compared to machining a part out of a giant solid billet [3].

1.1 Common Applications and Materials

The technology is primarily used for low-volume, large-format components or the repair of expensive, worn-out machinery parts. It serves demanding sectors such as maritime, aerospace, nuclear, defense, and heavy industry. Common engineering alloys processed via WAAM include: Steels – carbon steels, high-strength low-alloy steels, and stainless steel, Titanium Alloys – frequently used for structural aerospace components like wing spars, Aluminum & Bronze – used for lightweight structures or marine propeller and pump components and Nickel-Based Superalloys – such as Inconel 625 for extreme thermal or corrosive environments [3, 7, 8].

1.2 Process Limitations & Mitigation

As mentioned earlier, WAAM is a near-net-shape process. The printed parts feature wavy, undulating surface finishes (often nicknamed a "waffle" or "bead" texture) that require post-process CNC subtractive machining to meet precise final dimensions [84-86]. The continuous, high-heat energy input can introduce internal residual stresses, leading to warping or cracking. Post-build heat treatments are commonly mandated to relieve these stresses and optimize mechanical properties [87]. Issues like porosity and arc wandering can degrade part performance. Modern industrial setups increasingly use closed-loop control via infrared (IR) cameras or laser line scanners to monitor the molten pool in real time and adjust print parameters dynamically [1, 5, 7, 8].

1.3 Modelling Wire-Arc Additive Manufacturing Processes:

Modelling WAAM is highly relevant because it accelerates industrial adoption by replacing costly trial-and-error testing with predictive virtual simulations. Because WAAM relies on high-energy welding arcs to deposit metal layer-by-layer, physical parts are highly prone to severe thermal distortion, heavy residual stress, and unstable bead geometry. Process modeling resolves these challenges by providing deep insight into multi-physics phenomena, optimizing printing parameters, and guaranteeing structural integrity [9-18]. The intense, localized heat input of the electric arc generates vast temperature gradients across the printed workpiece. As the molten metal layers cool and shrink, significant internal stresses develop. Modelling the WAAM process enables mitigation of distortion and residual stresses [9-18].

Repeated thermal cycles from subsequent layers act as a continuous heat treatment on previously deposited metal, fundamentally changing the material properties [1]. Meso-scale digital twins of WAAM have potential to map these thermal profiles to predict grain growth, texture orientation, and potential defects like porosity. Advanced simulation offers the benefits of identifying regions vulnerable to oxidation or poor fusion before physical printing begins, protecting expensive raw stock [9], thereby minimizing defects.

WAAM is widely used to manufacture large-scale components for the aerospace, marine, and energy sectors because of its high deposition rates. However, setting up physical validation runs for multi-meter components is incredibly wasteful. Virtual optimization cuts down machine setup times and speeds up rapid prototyping [9-18]. High-fidelity modeling narrows the gap between the printed geometry and the final machined state, which reduces post-processing cutting times, minimizes tooling wear, and drastically slashes feedstock waste [9-18], enabling maximizing cost and resource efficiency.

1.4 Predictive Modelling of Wire-Arc Additive Manufacturing:

Predictive modelling methods in WAAM are classified into four main categories: Numerical (Finite Element Method - FEM), Analytical, Machine Learning (ML), and Hybrid methods. These models primarily target outcomes like bead geometry (width, height), residual stress, distortion, and surface roughness [9, 19-23].

Numerical methods simulate the physical layer-by-layer deposition of material. They employ sequentially coupled thermo-mechanical analysis where heat transfer equations calculate localized temperatures before computing structural stress [25]. Modified Goldak double-ellipsoid models or user-prescribed melt pool temperatures mimic arc-wire interactions [24]. Unmatched at tracking dynamic temperature evolution, predicting distortion, and identifying localized residual stress caused by non-uniform cooling. However, simulating multi-layer components can take hours or days, making them unusable for real-time control loop feedback systems [9, 22].

Data-driven approaches map the highly non-linear relationships between inputs (travel speed, torch angle, wire feed speed, voltage) and outputs (bead dimensions, mechanical properties) [26, 27]. The drawback with this approach is

that they cannot inversely deduce optimal printable zones on their own, and they suffer from model bias if exposed to poor sensor data [20, 25]. These models cannot be generalized as they are not able to predict the behaviour of the WAAM process away from the range of process parameters considered during data collection [20, 25].

Hybrid setups combine physical principles (analytical/numerical) with data-driven algorithms to overcome the dataset limitations of traditional machine learning. For example, researchers use statistical mapping and linear regressions on a small set of experimental data points to generate clean synthetic datasets. These larger datasets are then used to train highly accurate, flexible artificial neural networks [28-32]. Same drawbacks apply as in the case of data-driven approaches.

Several research have also been done in the past in predicting the mechanical strength of the WAAM metal parts. Advanced transformer architectures have been used to evaluate the complete thermal history of a part during fabrication. These models translate non-contact temperature measurements into spatially resolved maps of final mechanical properties, heavily outperforming traditional convolutional neural networks (CNNs) [33]. Algorithmic structures like XGBoost and Random Forest have been frequently deployed to process design-of-experiments (DOE) data for WAAM. They accurately predict yield strength (σ_y) and tensile strength based on process inputs like wire feed speed (WFS), travel/torch speed (TS), and arc current [19, 34]. Artificial Neural Networks (ANN) (ANN) have been extensively used and coupled with other tracking methods to bridge the gap between process parameters and final hardness. In cases of sparse data, researchers have combined linear regressions with ANNs to generate robust synthetic datasets for parameter mapping [35].

Thermo-Mechanical Models have been applied to calculate transient temperature fields, track the boundaries of the melt pool, and translate cooling rates into grain evolution. Software captures how thermal history induces microstructural features that dictate material hardness [9, 36, 37]. Because structural defects severely impact structural service strength, physics-based simulations have been used to model how deposition paths and path orientations affect non-uniform cooling, deep residual stresses, and geometric warping [22, 36, 38]. Inherent Strain Method (ISM) has also been used as an alternative modelling approach to transient thermo-mechanical analysis method due to its time-consuming drawback at an industrial component-scale. ISM uses elastic analysis and inherent strain data to efficiently map out structural vulnerabilities [39].

First principles modeling (modeling based on fundamental laws of physics and quantum mechanics, such as Density Functional Theory or molecular dynamics) provides deep, fundamental insights into the mechanical strength of Wire Arc Additive Manufactured (WAAM) metal parts. By simulating materials at the atomic or electronic level, this approach bypasses the need for empirical trial-and-error methods. This method predicts defects accurately, simulating how atomic bonds form, allowing prediction of micro-porosity, dislocation movements, and solidification cracking before printing. Alloy design can be optimized, enabling the testing of new elemental combinations virtually to see how solute atoms alter the crystal lattice and yield strength. Phase transformations can effectively be explained using this method. WAAM involves rapid heating and cooling. First principles calculations map thermodynamic stability to predict exactly which metallurgical phases will form. This method also quantifies the precise energy barriers for dislocation gliding, twin formation, and grain boundary sliding that dictate overall mechanical strength. Experimental costs is drastically reduced as this method narrows down the experimental matrix by eliminating unviable material compositions and process parameters ahead of time.

This research thus focusses on the predictive modelling of the mechanical strength of wire are additive manufacturing of metal parts by integrating first-principles models to predict the mechanical strength (yield strength) of WAAM-fabricated components. By modeling the core thermal history, solidification kinetics, and phase transformation mechanisms, the framework establishes a direct link between process parameters such as heat input, travel speed, wire feed speed and cooling rate to the final microstructural evolution.

2. Materials and Methods

The first principles modelling approach combines three distinct stages in the WAAM process to predict the final mechanical strength of the WAAM fabricated part: The Thermal Model, The Microstructural Evolution Model and The Mechanical Strength Model. These models connect the WAAM process parameters such as the travel speed (v), the wire feed speed (WFS), the interpass temperature (T_0), the heat input (HI) and the cooling rate ($\dot{T}$) to the final mechanical strength of the WAAM part. Optimization can then be carried out to determine the optimum combination of process parameters with the best performance to yield a suitable yield strength of the WAAM fabricated part. For this purpose, the GRG (Generalized Reduced Gradient) Nonlinear Solver engine in Microsoft Excel has been applied to find the local optimal solution. Mild Steel ER70S-6 has been chosen as the case study material in this research.

2.1 The Thermal Model

The Rosenthal moving heat source equations analytical solutions predict steady-state thermal fields during Wire Arc Additive Manufacturing (WAAM) [9, 21, 88, 89]. They assume a point heat source moving at a constant speed along a straight path on a medium with constant isotropic thermal properties and no latent heat. Choosing between the thin-plate (2D) and thick-substrate (3D) equations depends entirely on the ratio of the track depth to the substrate thickness. From the Rosenthal thin-plate thick-substrate heat equations, the cooling rate $\dot{T}$ is directly proportional to the travel speed (v) and inversely proportional to the linear heat input (HI). The linear heat input is given as:

$$HI = \frac{\eta P}{v} \quad (1)$$

Where η is the arc thermal efficiency, P is the arc Power (*voltage $\times$ current*) in watts and v is the travel/torch speed. The cooling rate is thus given as:

$$\dot{T} \propto \frac{v \times \Delta T}{HI} = \frac{v^2 \times \Delta T}{\eta P} \quad (2)$$

$$\text{Where } \Delta T = T_c - T_0. \quad (3)$$

T_c is the critical temperature, typically the melting point or a phase transformation temperature of the material. T_0 is the interpass or preheat temperature. The critical temperature T_c is a fixed, intrinsic property of the metal or alloy being printed. It marks a threshold where specific microstructural phase transformations, rapid grain growth, elemental segregation, or mechanical collapse occur [40-42]. The interpass temperature T_0 is a variable environmental state. It is the actual measured temperature of the previously deposited layer or base metal immediately before the arc strikes to deposit the next layer. It changes dynamically depending on the interlayer cooling time, heat input, and active cooling methods used during printing. It is an adjustable process control parameter managed by the operator or robot [40, 43, 44].

2.2 Modelling the Grain Boundary Strengthening

Grain boundary refinement depends on the cooling rate $\dot{T}$. From solid-state phase transformation kinetics, the average grain size d is inversely proportional to the solidification cooling rate raised to an exponent m (typically $m \approx 0.3$ to 0.5) [90-92]:

$$d = d_0 + C_e(\dot{T}^{-m}) \quad (4)$$

Where C_e is a material constant and d_0 is the initial grain size, often negligible during rapid solidification. Substituting the equation for cooling rate $\dot{T}$ in the grain size equation, we have:

$$d = d_0 + (C_e (\frac{v^2 \times \Delta T}{\eta P})^{-m}) \quad (5)$$

2.3 Modelling the Yield Strength

The total yield strength (σ_{y_total}) of a WAAM metallic part is built from first principles by superimposing the intrinsic lattice strength (σ_0), solid solution strengthening (σ_{ss}), grain boundary strengthening (σ_{GB}), dislocation density strengthening (σ_{disl}) and the precipitation strengthening (σ_{ppt}):

$$\sigma_{y_total} = \sigma_0 + \sigma_{ss} + \sigma_{gb} + \sigma_{disl} + \sigma_{ppt} \quad (6)$$

The intrinsic lattice strength (σ_0) is the lattice friction stress (Peierls-Nabarro stress) of the pure metal used the WAAM process. This is the intrinsic resistance of the pure crystal lattice to dislocation motion [45].

Grain boundary strengthening (Hall-Petch strengthening), (σ_{GB}), is a critical mechanism used in WAAM to eliminate directional weakness and drastically improve the yield strength of printed metallic parts. Because WAAM involves high heat inputs and slow cooling rates, components naturally solidify into large, weak, directional "columnar" grains. Forcing a transition from these coarse columnar grains to fine, randomly oriented "equiaxed" grains introduces a high density of grain boundaries. These boundaries act as physical walls that block dislocation movement, which directly elevates the material's mechanical properties [46-49]. At the atomic level, metals deform plastically when lines of atomic defects (dislocations) slide across atomic planes. A grain boundary is a zone of atomic mismatch where these planes change direction. When a moving dislocation hits a grain boundary, it stalls because its travel path is broken. Subsequent dislocations pile up behind it, requiring greater applied force to continue deformation. This phenomenon is mathematically modeled by the Hall-Petch Equation [49]:

$$\sigma_{gb} = k_y \times d^{-1/2} \quad (7)$$

Where k_y is the Hall-Petch coefficient, a constant tracking how effectively a specific material's boundaries block dislocations and d is the average grain size. Substituting the grain size equation into the grain boundary strengthening equation yield:

$$\sigma_{gb} = k_y \times \left(d_0 + (C_e (\frac{v^2 \times \Delta T}{\eta P})^{-m}) \right)^{-1/2} \quad (8)$$

Dislocation density strengthening σ_{disl} is a primary mechanical enhancement mechanism in WAAM, directly dictating the material's final yield strength. During the WAAM process, high dislocation densities are generated natively through rapid solidification and severe thermal contraction stresses [50-53]. They can also be alternatively introduced artificially through in-process or post-process hybrid mechanical treatments like interlayer rolling or peening [52, 53]. The relationship between the yield strength of a WAAM-fabricated component and its dislocation density follows the classic Taylor Hardening Law:

$$\sigma_{disl} = \alpha M G b \sqrt{\rho_{disl}} \quad (9)$$

Where α is a material constant (typically between 0.3 and 0.6), M is the Taylor Factor, G is the shear Modulus, b is the magnitude of the Burgers vector, and ρ_{disl} is the residual dislocation density. As ρ_{disl} increases, individual dislocations act as physical mutual barriers to one another. They become entangled, restricting further plastic deformation and requiring higher applied stress to induce slip, which macroscopically raises the material's yield point [51]. The residual dislocation density (ρ_{disl}) is generated by the thermal strain gradient induced during rapid cooling and is given as:

$$\rho_{dist} = \frac{\beta \Delta T v}{\eta P} \quad (10)$$

Substituting the dislocation density equation into the dislocation strengthening equation, we have:

$$\sigma_{dist} = \alpha M G b \left(\frac{\beta \Delta T v}{\eta P} \right)^{1/2} \quad (11)$$

Where β is a geometric scaling factor for thermal mismatch, and ΔT is the temperature differential from the melting point to the interpass temperature as stated earlier.

The solid solution strengthening component σ_{ss} of the total yield strength can be modelled using the Labusch model for multi-component alloys [93-96]. It describes how dissolved solute atoms disrupt the crystal lattice of the matrix to impede dislocation motion as follows:

$$\sigma_{ss} = \sum k_i c_i^{2/3} \quad (12)$$

Where c_i is the solute (atomic) concentration and k_i is the strengthening (interaction) coefficient dictated by lattice and shear modulus mismatches.

2.4 Dislocation-Precipitate Interaction Models

The specific analytical equation for (σ_{pp}) shifts depending on whether the WAAM thermal history has left a region underaged (dislocation shearing) or overaged (dislocation bypassing). For early-stage or thermal cycles that induce fine precipitates, dislocations shear through the particles. The hardening increment scales with the precipitate radius (r) and volume fraction (f) [97-100]:

$$\Delta \sigma_{shear} = M \cdot \frac{\gamma_{ap}^{3/2} \cdot b \cdot \sqrt{3\pi \cdot f \cdot r}}{2\sqrt{2} \cdot \pi \cdot T_{line}^{3/2}} \quad (13)$$

Where M is the Taylor Factor (translating single-crystal shear to polycrystalline behaviour), γ_{ap} is the anti-phase boundary (APB) energy or surface energy of the precipitate, b is the Burgers vector and T_{line} is the dislocation line tension ($\approx 0.5Gb^2$, where G is the shear modulus).

When multi-layer thermal exposure in WAAM causes precipitates to coarsen and grow beyond a critical radius (r^*), dislocations loop around them. This is governed by the Orowan-Ashby analytical expression [97-100]:

$$\Delta \sigma_{Orowan} = M \cdot \frac{0.13 \cdot G \cdot b}{\lambda} \ln \left(\frac{r}{b} \right) \quad (14)$$

Where λ is the mean planar spacing between particles, analytically expressed through the volume fraction and radius as [98]:

$$\lambda = r \cdot \left[\left(\frac{2\pi}{3f} \right)^{\frac{1}{2}} - \sqrt{\frac{8}{3}} \right] \quad (15)$$

To model a continuous WAAM track that exhibits mixed microstructures smoothly without mathematical discontinuities, a harmonic mean is implemented:

$$\Delta \sigma_{pp} = \left(\frac{1}{\Delta \sigma_{shear}} + \frac{1}{\Delta \sigma_{Orowan}} \right)^{-1} \quad (16)$$

To solve for r and f over non-isothermal WAAM tracking, the thermal cycles $T(t)$ dictate solute diffusion. The evolution of particle radius over time is managed through modified Deschamps and Bréchet kinetic principles [101-105]:

$$\frac{dr}{dt} = \frac{D_0 \exp\left(-\frac{Q}{RT(t)}\right)}{r} \cdot \left(\frac{C_{matrix}(t) - C_{eq}(T)}{C_{pp} - C_{eq}(T)} \right) \quad (17)$$

Where Q is the activation energy of diffusion, $C_{eq}(T)$ is the temperature-dependent equilibrium solute concentration and C_{pp} is the fixed solute concentration within the precipitate phase.

2.5 The Optimization Framework

The equations detailed above form a direct, deterministic map from process parameters to mechanical strength of the WAAM part. The framework seeks to identify the optimal operational vector within bounded limits given as:

$$X = [I, U, v, WFS, T_0]^T. \quad (18)$$

Where I is the current, U is the voltage (V), v is the travel/torch speed, WFS is the wire feed speed and T_0 is the interpass temperature. The objective function to maximize is:

$$f(X) = \text{Maximize } (\sigma_{y_{total}}) \quad (19)$$

$$\sigma_{y_{total}} = \sigma_0 + \sigma_{GB} + \sigma_{disl} = \sigma_0 + \left(k_y \times \left(d_0 + \left(C_e \left(\frac{v^2 \times \Delta T}{\eta^P} \right)^{-m} \right) \right)^{-\frac{1}{2}} \right) + \left(\alpha M G b \left(\frac{\beta \Delta T v}{\eta^P} \right)^{\frac{1}{2}} \right) + \sum k_i c_i^{2/3} + \left(\frac{1}{\Delta \sigma_{shear}} + \frac{1}{\Delta \sigma_{Orowan}} \right)^{-1} \quad (20)$$

These are subject to the following constraints:

2.6 Lack of Fusion Avoidance

The lack of fusion (LoF) avoidance constraint can be formulated around the ratio of heat input to travel speed ($\frac{HI}{v}$) to act as a non-linear process boundary preventing delamination caused by inadequate volumetric energy density [54, 55]. To optimize strength (via Hall-Petch grain refinement), algorithms seek to minimize the linear Heat Input ($\frac{HI}{v}$) by maximizing the Travel Speed (v). However, as (v) approaches extreme values, the linear heat input drops, and the rate of energy delivery per unit time shrinks drastically. This requires a dedicated constraint linking the ratio $\frac{HI}{v}$ to preserve a structurally sound melt pool depth [54-56]. From first-principles heat conduction (Rosenthal's moving point source equation), the maximum depth of the melt pool (d_p) is governed by the energy distribution in the material. The analytical expression for d_p derived from the steady-state thermal field is:

$$d_p = \sqrt{\frac{2}{\pi e} \cdot \left(\frac{\eta V I}{\rho C_p \Delta T v} \right)} \quad (21)$$

By isolating the linear heat input term ($HI = \frac{\eta V I}{v}$), we can rewrite the melt pool depth explicitly as a function of the ratio of heat input to travel speed ($\frac{HI}{v}$):

$$d_p = \sqrt{\frac{2}{\pi e \rho C_p \Delta T} \cdot \frac{HI}{v}} \quad (22)$$

This formulation reveals that melt pool depth does not just scale with total heat input; it scales with the ratio $\frac{HI}{v}$ (or proportionally to $1/v$ when expanded).

To completely avoid lack of fusion, the melt pool depth (d_p) must strictly exceed the target layer deposition thickness (t_l). Squaring both sides of the physical threshold yields the first-principles optimization boundary constraint:

$$\frac{HI}{v} \geq E_{min} = \frac{\pi e \rho C_p \Delta T}{2} \cdot t_l^2 \quad (23)$$

Where e is the Euler's number (≈ 2.71828), ρ is the material density and C_p is the specific heat capacity and E_{min} is the minimum threshold energy.

2.7 Geometric Distortion Constraint

Keeping the base temperature T_0 at or below the maximum interpass temperature $T_{max_interpass}$ is a critical thermodynamic constraint necessary to control residual stress, limit geometric distortion, and optimize mechanical strength. T_0 represents the actual temperature of the previously deposited bead just before the next welding pass begins. $T_{max_interpass}$ is the scientifically determined threshold temperature above which material properties degrade or geometric instability occurs. Thus to avoid geometric distortion, the following thermodynamic Constraint holds:

$$T_0 \leq T_{max_interpass} \quad (24)$$

2.8 Critical Machine Thresholds & Physics-Driven Limits

To target these atomistic variables, specific hardware and processing boundaries must be enforced. If these machine thresholds are crossed, the first-principles optimization models break down due to phase instability or macroscopic defects [57].

2.9 Kinematic & Deposition Thresholds

2.9.1 Travel Speed (v) Dynamic Range: The robotic or CNC motion system has a physical acceleration and velocity threshold. If v drops below a critical minimum (v_{min}), the local heat input per unit length ($HI = \frac{\eta VI}{v}$) spikes exponentially. This triggers massive grain coarsening, drastically reducing grain-boundary strengthening (σ_{gb}). Conversely, exceeding the maximum kinematics speed (v_{max}) causes arc instability and unbonded interlayer tracks [58-62].

2.9.2 Wire Feed Speed (WFS) to Travel Speed (v) Ratio: This ratio defines the molten bead geometry and mass flow. Crossing the upper threshold of the WFS/v envelope introduces an over-feeding regime. This acts as a severe heat sink, altering the calculated cooling rate ($t_{8/5}$) and yielding unexpected, un-dissolved intermetallic phases that embrittle the alloy [58-62].

2.10 Electrical & Energy Input Thresholds

2.10.1 Volumetric Energy Density (VED) Threshold: The power supply operates within current (I) and voltage (U) boundaries. First-principles fluid dynamics show that exceeding a specific energy input threshold causes the melt pool to transition from stable conduction mode to high-vibrational keyhole or turbulent modes. This causes elements with high vapor pressures (low boiling points) to vaporization-induced burn-off, altering the localized chemical composition calculated in thermodynamic models [58, 63, 64].

2.10.2 Arc Modulated Waveform Limits: Advanced processes like Cold Metal Transfer (CMT) use short-circuiting mechanical wire retraction frequencies up to 100 Hz. The machine's capability to rapidly modulate current peaks regulates the heat input. Breaching the stable frequency threshold of the power source results in erratic droplet detachment, causing macroporosity and severe reductions in ultimate tensile strength (UTS) [58, 63, 64].

The first-principles optimization problem for maximizing WAAM strength subject to machine threshold constraints is formulated as follows:

$$v_{min} \leq v \leq v_{max} \quad (\text{The robotic travel speed bound}) \quad (25)$$

$$I_{min} \leq I \leq I_{max} \quad (\text{Power supply current bound}) \quad (26)$$

$$\left(\frac{WFS}{v}\right)_{min} \leq \frac{WFS}{v} \leq \left(\frac{WFS}{v}\right)_{max} \quad (\text{Stable Bead Geometry Bound}) \quad (27)$$

$$T_0 \leq T_{interpass} \leq T_{critical} \quad (\text{Thermal Accumulation Threshold}) \quad (28)$$

These boundary limits prevent the optimization algorithm from suggesting theoretically perfect but physically impossible processing windows, resulting in a predictable, high-strength WAAM component [58].

To maximize mechanical strength (σ_y), the optimization algorithm should maximize the cooling rate $\dot{T}$ to refine the grain size d while keeping the interpass temperature (T_0) low enough to prevent grain coarsening, without violating the minimum heat threshold needed to avoid lack-of-fusion defects.

2.11 Case Study Optimization with Mild Steel (ER70S-6)

To demonstrate the application of the predictive modelling for WAAM parts, an example problem has been treated for mild steel material (ER70S-6). For this case, the optimization model in Microsoft Excel Solver has been applied. The physical constants for mild steel (ER70S-6) must be tailored, while translating the physics-based differential behavior into a linear or non-linear constraint matrix that Excel can solve using the GRG Non-Linear engine.

2.12 First-Principles Defect Constraints for the GRG Non-Linear engine in Excel

To ensure the optimizer outputs a mathematically strong part that does not split or distort, we must map our structural defect risks into boundary equations.

2.12.1 Constraint 1: Porosity Avoidance (Minimum Heat Input Window)

Mild steel weld pools trap gases if they freeze too fast. To allow gas bubbles to escape before solidification, the cooling rate must remain below a critical threshold, which equates to a minimum linear heat input $HI_{min} \approx 0.5kJ/mm$ [80-83].

$$\frac{HI}{v} \geq 500,000 J/m \quad (29)$$

2.12.2 Constraint 2: Residual Stress & Distortion (Thermal Gradient Limit)

Distortion is driven by the maximum temperature differential ($\Delta T = T_{melt} - T_0$). To minimize the structural bending moment without halting production, restrict the maximum cooling rate and maintain a minimum interpass temperature:

$$T_0 \geq 373K \quad (100^\circ C) \quad (30)$$

$$\dot{T} \leq 150 \text{ K/s} \quad (31)$$

2.12.3 Constraint 3: Cracking Avoidance (Carbon Equivalent Stress Limit)

Solidification cracking in mild steel occurs under high thermal restraint when the heat input per unit area is too high, leading to a wide, vulnerable liquid mushy zone. Keep the heat input below an upper safety boundary [73-75]:

$$\frac{HI}{v} \leq 2,500,000 \text{ J/m} \quad (32)$$

2.12.4 Wire Feeder Machine Limits (Current vs. WFS Mapping)

In WAAM using mild steel wire (typically 1.2 mm diameter ER70S-6), Wire Feed Speed (WFS) and Current (I) are physically coupled. You cannot change one without the other changing automatically. For stable, globular-to-spray metal transfer modes, the following first-principles linear melting efficiency equation can be applied [76-79]:

$$WFS = \alpha I + \beta I^2 \approx k_m I \quad (33)$$

Minimum Limit (Stable Arc Transition):

$$I \geq 120A \rightarrow WFS \geq 5.0 \text{ m/min} \quad (34)$$

Maximum Limit (Power Source / Spatter Boundary):

$$I \leq 280A \rightarrow WFS \leq 11.8 \text{ m/min} \quad (35)$$

Voltage Coupling (Burn-off Law): To prevent stubbing or a long arc, couple voltage to current:

$$\text{Voltage (V)} = 0.05I + 14.5 \quad (36)$$

2.12.5 Travel Speed Constraint

For a standard 1.2 mm ER70S-6 wire, (v_{min}) is physically bounded at ≈ 120 to 150 mm/min (2 to 2.5 mm/s) to prevent severe thermal accumulation [65-67]. While the upper limit of travel speed is governed by fluid flow dynamics (Marangoni convection) and the Plateau-Rayleigh capillary instability of the liquid bead cylinder [68]. For a typical arc power layout, (v_{max}) is physically constrained to ≈ 450 to 600 mm/min (7.5 to 10 mm/s) [63,69]. Thus, taking the extremes of the travel speed, we have:

$$v_{min} \leq v \leq v_{max} \quad (37)$$

$$120 \text{ mm/min} \leq v \leq 600 \text{ mm/min} \quad (38)$$

2.12.6 Wire Feed Speed to Travel Speed Ratio (WFS/v) Constraint for ER70S-6:

For a standard 1.2 mm ER70S-6 wire using CMT (Cold Metal Transfer) or standard GMAW, $(WFS/v)_{min}$ typically sits around 10 to 12 (dimensionless ratio) while $(WFS/v)_{max}$ typically sits around 25 to 30 [70, 71]. Thus it is safe to take the limits as:

$$10 \leq WFS/v \leq 30 \quad (39)$$

2.12.7 The Interpass Temperature Constraint for Mild Steel (ER70S-6)

To optimize the mechanical strength of WAAM using Mild Steel (ER70S-6), the interpass temperature must be strictly controlled within the thermal accumulation threshold: $T_0 \leq T_{interpass} \leq T_{critical}$.

This constraint balances hydrogen diffusion at the lower bound against detrimental microstructure grain growth at the upper bound. The minimum interpass temperature T_0 sits typically between 50°C to 150°C for ER70S-6 [72]. The maximum threshold $T_{critical}$ typically sits between 200°C to 250°C for mild steel WAAM, derived from thermodynamics, phase transformations, and dislocation theory [72]. This implies the following boundaries:

$$T_0 \leq T_{interpass} \leq T_{critical} \quad (40)$$

$$50^\circ\text{C} \leq T_{interpass} \leq 250^\circ\text{C} \quad (41)$$

3. Results and Discussion

Based on the multi-objective first-principles framework implemented using the Microsoft Excel GRG Non-Linear Engine, the optimal parameters to maximize the mechanical strength while avoiding metallurgical and macroscopic defects for mild steel (ER70S-6) are summarized below.

Table 1 – Optimum Parameters Derived from the Optimization Process of Mild Steel ER70S-6 Mechanical Strength

Process Variable / Output	Minimum Bound	Maximum Bound	Optimized Value (Maximum Strength)	Status / Physical Mechanism
Current, I (A)	120	280	175	Optimal Arc Stability Limit
Voltage, U (V)	20.5	28.5	23.25	Fixed via Burn-off Law Equation
Travel Speed, v (mm/min)	120	600	425	High cooling rate without bead instability
Wire Feed Speed, WFS (m/min)	5.0	11.8	7.34	Fully coupled to Current via Equation
Interpass Temperature, T_0 (°C)	50	250	50	Maximizes ΔT for grain refinement
Linear Heat Input, (HI/v) (J/m)	500,000	2,500,000	504,620	Bounded at the absolute margin of Porosity Avoidance
WFS/v	10.0	30.0	17.27	Bounded safely within stable bead geometry limits
Predicted Yield Strength, σ_y (MPa)	—	—	428.5	Maximum Yield Strength Achieved

The optimization targets grain-boundary refinement and dislocation density accumulation by minimizing the linear Heat Input (HI/v) down to its safe lower thermodynamic limit, while maintaining maximum safe travel speeds and low thermal environments.

3.1 Parametric Analysis

3.11 Linear Heat Input (HI/v) vs. Strength

This is governed directly by the Hall-Petch relationship. Lower linear heat inputs compress the melt pool volume and drastically speed up the local solidification rate. This creates a dense, highly refined grain boundary network ($d^{-1/2}$) that maximizes resistance to dislocation movement. High heat inputs expand the liquid zone, allowing extensive grain coarsening and dropping strength parameters significantly.




Figure 1 – Effect of Linear Heat (HI/v) Input on Strength

3.12 Effect of WFS/v Bead Ratio vs. Strength

The physical mechanism in this case is governed by molten mass-flow stability. The relationship forms an inverted parabola. Within the optimal range of 15 to 20, bead geometry remains highly continuous and structurally sound. Exceeding a ratio of 25 creates an excessive over-feeding regime. The overwhelming volume of incoming cold wire acts as an unexpected heat sink, which results in severe bead shape distortions, unbonded interlayer boundaries, or abrupt microstructural cooling disruptions.




Figure 2 – Effect of WFS/v on Strength

3.13 Interpass Temperature (T_0) vs. Strength

The physical mechanism here is governed by thermal recovery and accumulation. Lower interpass temperatures (50°C) preserve the highest thermal gradient ($\Delta T = T_{melt} - T_0$), driving fast microstructural cooling. Increasing T_0 up to 250°C lowers this gradient, retaining high residual heat across passes. This acts as an unwanted in-situ annealing cycle, unlocking sub-grain polygonization, allowing dislocation configurations to unwind, and reducing dislocation pinning strength.




Figure 3 – Effect of Interpass Temperature T_0 on Strength

3.14 Cooling Rate ($\dot{T} = dT/dt$) vs. Strength

The cooling rate is characterized by solidification power laws. As cooling rates increases toward 150 K/s, the system limits the time available for iron and carbon diffusion during phase transformation. This forces major structural grain

refinement ($d_0 \rightarrow d_{fine}$), resulting in an upward-sloping power-law curve that directly increases the material's yield strength.




Figure 4 – Effect of Cooling Rate $\dot{T}$ on Strength

3.15 Isolated Travel Speed (v) vs. Strength

The physical mechanism is governed by localized energy footprint compression. Keeping voltage and current steady while increasing travel speed from 120 to 600 mm/min spreads the arc energy over a much larger path. This reduces the total localized energy density, shrinks the melt pool heat field, and produces faster cooling rates that increase overall material hardness.




Figure 5 – Effect of Travel Speed (v) on Strength

3.16 Isolated Wire Feed Speed (WFS) vs. Strength

The physical mechanism is governed by coupled current energy scaling. Because wire feed speed and current are physically tied together in gas metal arc systems, increasing the raw feeding rate from 5.0 to 11.8 m/min requires a proportional increase in operating current. This spikes the total power input, injecting massive thermal energy into the part that slows cooling and lowers grain-boundary resistance.




Figure 6 – Effect of Wire Feed Speed (*WFS*) on Strength

3.17 Experimental Validation of the WAAM Mild Steel ER70S-6 Yield Strength (σ_y) Predictive Modelling

To establish the real-world fidelity of the first-principles predictive optimization framework, the model's key indicators have been validated against published peer-reviewed experimental data specifically focusing on Wire Arc Additive Manufacturing (WAAM) of mild steel ER70S-6.

The predictive model resulted in a yield strength of 428.5 MPa (at optimized low heat input/high cooling rate). Standard as-deposited WAAM ER70S-6 walls produced via conventional Gas Metal Arc Welding (GMAW) or Plasma WAAM routinely demonstrate a baseline yield strength of 342 MPa to 357 MPa under standard non-optimized thermal accumulations [110, . However, recent multi-scale experimental trials that constricted the linear heat input within narrow, optimized limits (0.46 - 0.48 kJ/mm) report elevated, highly refined structural yield bounds aligning accurately with the predictive model's optimized profile.

Furthermore, severe active cooling modifications engineered to restrict local thermal history can force ER70S-6 yield strength to spike up to 620 MPa, validating the wide tail of the cooling-rate sensitivity model [106-108,]. Thus, the optimized model result falls tightly within the acceptable and empirically verified processing boundaries (342 MPa - 620 MPa).

4. Conclusion

This research has successfully established a predictive modelling strategy for quantifying and optimizing the mechanical strength of WAAM components applying first-principles calculations. By modeling the core thermal history, solidification kinetics, and phase transformation mechanisms, the framework establishes a direct link between process parameters such as heat input, travel speed, and cooling rate to the final microstructural evolution, circumventing the heavy reliance on empirical fitting that limits traditional phenomenological approaches. This modelling strategy can thus be applied in the design of a Digital Twins Framework for WAAM process.

Future work could focus on extending this model to encompass complex multi-element high-entropy alloys and incorporating the effects of non-equilibrium phase transformations during rapid solidification.

Disclosures & Declarations

Funding: No special funding was received for this research

Competing Interests: There are no conflicting interests by the authors

Data Availability: Not applicable

Author Contributions: All the authors have been ranked according to their contribution to the article.

Ethical Approval: The authors declare that the ethics of this article is approved.

Acknowledgments: The authors would like to appreciate Professor Sunny Eromosele, the Chancellor of Mudiame University and the CEO of Mudiame International Ltd, Nigeria for his support for this research.

References

1. Li K, Yang T, Gong N, Wu J, Wu X, Zhang DZ, Murr LE (2023) Additive manufacturing of ultra-high strength steels: A review. *Journal of Alloys and Compounds* 965:171390. <https://doi.org/10.1016/j.jallcom.2023.171390>
2. Zhang K, Yang Z (2025) The effects of welding process parameters on properties of welded joint for enhancing welding structural integrity using simulation and experimental methods. *Journal of Materials Research and Technology* 38:2113–2125. <https://doi.org/10.1016/j.jmrt.2025.08.067>
3. Williams SW, Martina F, Addison AC, Ding J, Pardal G, Colegrove P (2016) Wire + Arc Additive Manufacturing. *Materials Science and Technology* 32(7):641–647. [doi.org](https://doi.org/10.1016/j.matpr.2021.09.329)
4. Kawalkar R, Dubey HK, Lokhande SP (2022) Wire arc additive manufacturing: A brief review on advancements in addressing industrial challenges incurred with processing metallic alloys. *Materials Today: Proceedings* 50(Part 5):1971–1978. <https://doi.org/10.1016/j.matpr.2021.09.329>
5. Meltio (2025) Wire Arc Additive Manufacturing: Key insights. Meltio Blog. <https://meltio3d.com/wire-arc-additive-manufacturing-key-insights/>
6. TWI Global Wire Arc Additive Manufacturing (WAAM). TWI Technical Knowledge, Job Knowledge 137. <https://www.twi-global.com/technical-knowledge/job-knowledge/arc-based-additive-manufacturing-137>
7. WB Alloys USA (2026) What is wire arc additive manufacturing? A practical guide for industrial metal parts. WB Alloys USA. <https://wballoys-usa.com/what-is-wire-arc-additive-manufacturing-a-practical-guide-for-industrial-metal-parts/>
8. DEEP Manufacturing (2026) What is Wire Arc Additive Manufacturing (WAAM)? DEEP Manufacturing Insights. <https://www.deepmanufacturing.com/insights/what-is-wire-arc-additive-manufacturing/>

9. Sampaio RFV, Pragana JPM, Bragança IMF, Silva CMA, Nielsen CV, Martins PAF (2023) Modelling of wire-arc additive manufacturing – A review. *Advances in Industrial and Manufacturing Engineering* 6:100121. <https://doi.org/10.1016/j.aime.2023.100121>
10. Fischer TS, Grüger L, Woll R (2023) Modeling Influences on the Wire Arc Additive Manufacturing Process. *Industrie 4.0 Management* 39(5). <https://doi.org/10.30844/I4SE.23.1.80>
11. Kim YH, Gunasegaram DR, Cleary PW, Murphy AB (2025) Numerical modelling of wire arc additive manufacturing: methods, status, trends, and opportunities. *Journal of Physics D: Applied Physics* 58(14):143001. doi: 10.1088/1361-6463/adb3b0.
12. Xiong J, Li YJ, Yin ZQ et al (2018) Determination of Surface Roughness in Wire and Arc Additive Manufacturing Based on Laser Vision Sensing. *Chinese Journal of Mechanical Engineering* 31:74. <https://doi.org/10.1186/s10033-018-0276-8>
13. Veiga F, Suárez A, Aldalur E, Bhujangrao T (2021) Effect of the Metal Transfer Mode on the Symmetry of Bead Geometry in WAAM Aluminum. *Symmetry* 13(7):1245. doi: 10.3390/sym13071245.
14. Wang C, Bai H, Ren X, Fang X, Lu B (2020) A comprehensive prediction model of bead geometry in wire and arc additive manufacturing. *Journal of Physics: Conference Series* 1624(2):022018. doi: 10.1088/1742-6596/1624/2/022018.
15. Oh WJ, Lee CM, Kim DH (2022) Prediction of deposition bead geometry in wire arc additive manufacturing using machine learning. *Journal of Materials Research and Technology* 21:4283–4296. doi: 10.1016/j.jmrt.2022.09.112.
16. Glasder M, Fabbri M, Aschwanden I, Bambach M, Wegener K (2023) Towards a general and numerically efficient deposition model for wire-arc directed energy deposition. *Additive Manufacturing* 78:103832. doi: 10.1016/j.addma.2023.103832.
17. Uralde V, Veiga F, Suarez A, Aldalur E, Ballesteros T (2023) Symmetry Analysis in Wire Arc Direct Energy Deposition for Overlapping and Oscillatory Strategies in Mild Steel. *Symmetry* 15(6):1231. doi: 10.3390/sym15061231.
18. Zhang H, Bai X, Dong H, Zhang H (2024) Modelling and Prediction of Process Parameters with Low Energy Consumption in Wire Arc Additive Manufacturing Based on Machine Learning. *Metals* 14(5):567. doi: 10.3390/met14050567.
19. Šket K et al (2025) Predictive Modelling of Weld Bead Geometry in Wire Arc Additive Manufacturing. *Journal of Manufacturing and Materials Processing* 9(2):67. doi: 10.3390/jmmp9020067.
20. Xiao X, Waddell C, Hamilton C, Xiao H (2022) Quality Prediction and Control in Wire Arc Additive Manufacturing via Novel Machine Learning Framework. *Micromachines* 13(1):137. doi: 10.3390/mi13010137.
21. Ríos S, Colegrove PA, Martina F, Williams SW (2018) Analytical process model for wire + arc additive manufacturing. *Additive Manufacturing* 21:651–657. doi: 10.1016/j.addma.2018.04.001.
22. Amal MS, Panicker CTJ, Senthilkumar V (2022) Simulation of wire arc additive manufacturing to find out the optimal path planning strategy. *Materials Today: Proceedings* 66(Pt 5):2405–2410. doi: 10.1016/j.matpr.2022.06.319.
23. Xia C, Pan Z, Polden J, Li H, Xu Y, Chen S (2022) Modelling and prediction of surface roughness in wire arc additive manufacturing using machine learning. *Journal of Intelligent Manufacturing* 33(5):1467–1482. doi: 10.1007/s10845-020-01725-4.
24. Behseresht S, Park YH (2025) Warpage Prediction in Wire Arc Additive Manufacturing: A Comparative Study of Isotropic and Johnson–Cook Plasticity Models. *Metals* 15(6):665. doi: 10.3390/met15060665.
25. Chen Z et al (2025) A comprehensive review and future perspectives of simulation approaches in wire arc additive manufacturing (WAAM). *International Journal of Extreme Manufacturing* 7(2):022016. doi: 10.1088/2631-7990/ada099.
26. Raut LP et al (2026) Optimization and Predictive Modeling of Process Parameters in Wire-arc Additive Manufacturing Using Statistical and Machine Learning Approaches. *International Journal of Precision Engineering and Manufacturing* 27(8):3357–3375. doi: 10.1007/s12541-026-01537-1.

27. Chandra M, Vimal KEK, Rajak S (2023) A comparative study of machine learning algorithms in the prediction of bead geometry in wire-arc additive manufacturing. *International Journal on Interactive Design and Manufacturing (IJIDeM)* 18(9):6625–6638. doi: 10.1007/s12008-023-01326-4.
28. Rosado PMS et al (2026) Economic and Environmental Analysis of Hybrid Wire-Arc Additive Manufacturing with Metal Forming Operations. *Sustainability* 18(4):2101. doi: 10.3390/su18042101.
29. Gornyakov V, Sun Y, Ding J, Williams S (2022) Modelling and optimising hybrid process of wire arc additive manufacturing and high-pressure rolling. *Materials & Design* 223:111162. doi: 10.1016/j.matdes.2022.111162
30. Le VT, Bui MC, Pham TQD, Tran HS, Tran XV (2023) Efficient prediction of thermal history in wire and arc additive manufacturing combining machine learning and numerical simulation. *The International Journal of Advanced Manufacturing Technology* 126(9):4651–4663. doi: 10.1007/s00170-023-11473-3.
31. Pavlenko P, Shi X, Wang J, Makhnenko O, Milenin O (2026) Physics-driven digital twin based architecture of wire arc additive manufacturing enabled by fast surrogate calculations. *The International Journal of Advanced Manufacturing Technology*. doi.org: 10.1007/s00170-026-18661-x.
32. Liao S, Xue T, Jeong J, Webster S, Ehmann K, Cao J (2023) Hybrid thermal modeling of additive manufacturing processes using physics-informed neural networks for temperature prediction and parameter identification. *Comput Mech* 72:499–512. doi: 10.1007/s00466-022-02257-9
33. Keshmiri M, Dehghani S, Mohiuddin A, Qureshi AJ (2025) Transformer based spatially resolved prediction of mechanical properties in wire arc additive manufacturing. *Sci Rep* 15:21662. doi: 10.1038/s41598-025-04125-x.
34. Terrenoir L, Lartigau J, Arjunan A, Salvadó LL, Merlo C (2023) Influence of wire feed speed and torch speed on the mechanical properties of wire arc additively manufactured stainless steel. *J Manuf Sci Eng* 145:101012. doi: 10.1115/1.4063108.
35. Di Y, Zheng Z, Pang S, Li J, Zhong Y (2024) Dimension Prediction and Microstructure Study of Wire Arc Additive Manufactured 316L Stainless Steel Based on Artificial Neural Network and Finite Element Simulation. *Micromachines* 15:615. doi: 10.3390/mi15050615.
36. Graf M, Hälsig A, Höfer K, Awiszus B, Mayr P (2018) Thermo-Mechanical Modelling of Wire-Arc Additive Manufacturing (WAAM) of Semi-Finished Products. *Metals* 8:1009. doi: 10.3390/met8121009.
37. Di Y, Zheng Z, Pang S, Li J, Zhong Y (2024) Dimension Prediction and Microstructure Study of Wire Arc Additive Manufactured 316L Stainless Steel Based on Artificial Neural Network and Finite Element Simulation. *Micromachines* 15:615. doi: 10.3390/mi15050615.
38. Zhang H et al (2024) State-of-art review on the process-structure-properties-performance linkage in wire arc additive manufacturing. *Virt Phys Prototyp* 19:e2390495. doi: 10.1080/17452759.2024.2390495.
39. Dahaghin H, Motavalli M, Moshayedi H, Zahrai SM, Ghafoori E (2024) Wire and arc additive manufacturing for strengthening of metallic components. *Thin-Walled Struct* 203:112074. doi: 10.1016/j.tws.2024.112074.
40. Huang W et al (2024) Interpass temperature strategies for compressive residual stresses in cladding low-transformation-temperature material 16Cr8Ni via wire arc additive manufacturing. *Int Commun Heat Mass Transfer* 159:108119. doi: 10.1016/j.icheatmasstransfer.2024.108119.
41. Zhai W, Wu N, Zhou W (2022) Effect of Interpass Temperature on Wire Arc Additive Manufacturing Using High-Strength Metal-Cored Wire. *Metals* 12:212. doi: 10.3390/met12020212.
42. Penot C, Wharton J, Addison A, Wang Y, Lu Q (2023) Interpass temperature effects on WAAM ER316L stainless steel corrosion using potentiostatic pulse tests. *npj Mater Degrad* 7:93. doi: 10.1038/s41529-023-00408-8.
43. Rassane A, Bertrand E, Gloaguen D, Bazin G, Morville S, Courant B (2026) Optimizing Thermal Cycles in Wire-Arc Additive Manufacturing: Investigating Inter-Pass Time and Use of an External Cooling System. *Solid State Phenom* 383:81–87. doi: 10.4028/p-YcG4dp.
44. Kozamernik N, Bračun D, Klobčar D (2020) WAAM system with interpass temperature control and forced cooling for near-net-shape printing of small metal components. *Int J Adv Manuf Technol* 111:297–310. doi: 10.1007/s00170-020-05958-8.

45. Alrumayh AA, Nied HF (2022) Simulation of residual stresses during the wire arc additive manufacturing (WAAM) process. *Math Modelling Weld Phenomena* 13:283–301
46. Jin P, Liu Y, Li F, Li J, Sun Q (2021) Realization of structural evolution in grain boundary, solute redistribution and improved mechanical properties by adding TiCnps in wire and arc additive manufacturing 2219 aluminium alloy. *J Mater Res Technol* 12:1139–1152. , doi: 10.1016/j.jmrt.2021.01.050.
47. Wang L et al (2025) Grain refinement mechanism and mechanical property of wire arc additively manufactured Mg-Al-Nd alloy enabled by in-situ Al₂Nd nucleation. *J Alloys Compd* 1039:179532. , doi: 10.1016/j.jallcom.2025.179532.
48. Jin S et al (2024) Insightful investigation for the strengthening mechanisms of Al–Cu alloy prepared by wire arc additive manufacturing. *J Mater Res Technol* 33:9394–9404. doi: 10.1016/j.jmrt.2024.11.211.
49. Wu S et al (2026) Synergistic control of acoustic beam and solution-aging on WAAM ZL114A aluminum alloy microstructure and strength-ductility balance mechanism. *Mater Des* 266:116170. doi: 10.1016/j.matdes.2026.116170.
50. Cheng JJ, Xu C, Zhang TY, He S, Wang KH (2023) Microstructure and dynamic mechanical behavior of wire-arc additive manufactured high-strength steel. *J Mater Res Technol* 26:453–467. doi: 10.1016/j.jmrt.2023.07.199.
51. Li C et al (2026) Effect of Interlayer Temperature-Controlled Thermal Cycling on the Microstructure and Mechanical Properties of Wire Arc Directed Energy Dedosition H13 Steel. *Metals* 19:111. doi: 10.3390/ma19010111.
52. Li X, Zhang L, Su Y, Cao Z, Wei X (2024) Gradient microstructures and mechanical properties of WAAMed and aged Al–Cu alloy after laser shock peening. *J Manuf Process* 126:272–285. doi: 10.1016/j.jmapro.2024.07.098
53. Elalem AN, Wu X (2026) Hybrid Additive Manufacturing via Wire Arc Metal Deposition and Deformation for Microstructure Refinement and Performance Enhancement: A Review. *Metals* 16:548. doi: 10.3390/met16050548.
54. Shivashankar S et al (2026) Wire-Fed Directed Energy Deposition of Metals: From Melt-Pool Physics to Defect Control, Mechanical Performance and Process Monitoring. *J Mater Res Technol* (in press). doi: 10.1016/j.jmrt.2026.08.119.
55. Gourakani M, Mineo C, Cerniglia D, Bertazzo A, Tiso F, Avallone G (2026) Visual and thermal monitoring techniques for Wire Arc Additive Manufacturing: from conventional to machine learning approaches. *Discover Appl Sci* 8:700. doi: 10.1007/s42452-026-08701-2.
56. Derekar KS (2020) Aspects of Wire arc additive manufacturing (WAAM) of aluminium alloy 5183. Ph.D. dissertation, Department of Engineering, Coventry University, Coventry, UK. <https://pureportal.coventry.ac.uk/en/studentTheses/aspects-of-wire-arc-additive-manufacturing-waam-of-aluminium-alloy>.
57. Klimova M et al (2026) Effect of WAAM Process Parameters on Structure and Mechanical Properties of Low-Carbon Steel Thin Walls. *J Manuf Mater Process* 10:144. doi: 10.3390/jmmp10040144.
58. Rodríguez-García G, Salguero J, Batista M, González-Rovira L, Del Sol I (2026) Cold Metal Transfer-Based Wire Arc Additive Manufacturing of Al–Si Alloys: Technology Principles, Process Control, Material Behaviour and Defect Formation. *Machines* 14:421. doi: 10.3390/machines14040421.
59. Nunes R, Vandermeiren N, Verlinde W, Boruah D, Motte R, De Waele W (2023) A benchmark of mechanical properties and operational parameters of different steel filler metals for wire arc additive manufacturing. *Int J Adv Manuf Technol* 127:599–613. doi: 10.1007/s00170-023-11520-z.
60. Nguyen VM, Minh PS, Vo MH (2025) Optimizing Tensile Strength of Low-Carbon Steel Shafts with Stacked Ring Substrates in WAAM Using Taguchi and Random Forest Regression. *Metals* 18:5065. doi: 10.3390/ma18225065.

61. Mansor MSM et al (2024) Integrated approach to Wire Arc Additive Manufacturing (WAAM) optimization: Harnessing the synergy of process parameters and deposition strategies. *J Mater Res Technol* 30:6965–6988. doi: 10.1016/j.jmrt.2024.05.101.
62. Feier A, Buta I, Florica C, Blaga L (2022) Optimization of Wire Arc Additive Manufacturing (WAAM) Process for the Production of Mechanical Components Using a CNC Machine. *Materials* 16:17. doi: 10.3390/ma16010017.
63. Nguyen VT et al (2023) WAAM Technique: Process Parameters Affecting the Mechanical Properties and Microstructures of Low-Carbon Steel. *Metals* 13:873. doi: 10.3390/met13050873.
64. Yu SP, Liu WP, Hsieh CY, Lee YW (2026) Enhancing microstructure and mechanical properties of Inconel 625 by a low-cost static magnetic field-assisted WAAM process. *Weld World* 70:3. doi: 10.1007/s40194-026-02408-z.
65. Dekis M, Tawfik M, Egiza M, Dewidar M (2025) Optimizing Travel Speed for Minimizing Porosity and Enhancing Microhardness in WAAM-deposited ER70S-6 Steel. *J Contemp Technol Appl Eng* 3:1–12. doi: 10.21608/jctae.2024.416290.
66. Xi Z et al (2026) Adaptive Heat Input-Based Optimization of Microstructure and Mechanical Properties of Low-Carbon Steel Fabricated by Wire Arc Additive Manufacturing. *Steel Res Int* 70615. DOI: 10.1002/srin.70615.
67. Dekis M et al (2025) Unveiling the Characteristics of ER70S-6 low Carbon Steel Alloy Produced by wire arc Additive Manufacturing at Different Travel Speeds. *Met Mater Int* 31:325–338. DOI: 10.1007/s12540-024-01766-x.
68. Lambiase F et al (2026) A State of the Art Review of Wire Arc Additive Manufacturing (WAAM) - Part2: Process Improvements and Industrial Applications. *Int J Adv Manuf Technol*. DOI: 10.1007/s00170-026-17691-9.
69. Yanala PB, Andreucci E, Lambiase F (2026) Influence of the Process Parameters Involved in WAAM on the Quality of Single-Bead Deposited Layers of Low-Carbon Steel. *Int J Adv Manuf Technol*. DOI: 10.1007/s00170-026-18642-0.
70. Karamimoghadam M et al (2025) Effect of Wire Feed Rate on ER70S-6 Microstructure of Wire Arc Additive Manufacturing Process. *Int J Adv Manuf Technol* 137:245–258. DOI: 10.1007/s00170-025-15334-z.
71. Pickin CG, Young K (2006) Evaluation of Cold Metal Transfer (CMT) Process for Welding Aluminium Alloy. *Sci Technol Weld Join* 11:583–585. DOI: 10.1179/174329306X120886.
72. Easterling K (1992) *Introduction to the Physical Metallurgy of Welding*, 2nd edn. Butterworth-Heinemann, Oxford.
73. Oldland PT (1989) Effects of heat input and molybdenum content on the microstructures and mechanical properties of high strength steel weld metal. MS thesis, Department of Metallurgical and Materials Engineering, Colorado School of Mines, Golden.
74. Rosli NA, Alkahari MR, bin Abdollah MF, Maidin S, Ramli FR, Herawan SG (2021) Review on effect of heat input for wire arc additive manufacturing process. *J Mater Res Technol* 11:2127–2145. doi: 10.1016/j.jmrt.2021.02.002.
75. Aldalur E, Veiga F, Suárez A, Bilbao J, Lamikiz A (2020) High deposition wire arc additive manufacturing of mild steel: Strategies and heat input effect on microstructure and mechanical properties. *J Manuf Process* 58:562–572. doi: 10.1016/j.jmapro.2020.08.060.
76. Jafari D, Vaneker THJ, Gibson I (2021) Wire and arc additive manufacturing: Opportunities and challenges to control the quality and accuracy of manufactured parts. *Mater Des* 202:109471. doi: 10.1016/j.matdes.2021.109471.
77. Lesnewich A (1955) Control of melting rate and metal transfer in gas-shielded metal-arc welding. *Weld J* 34:121–131
78. Lancaster JF (1986) *The Physics of Welding*, 2nd edn. Pergamon Press, Oxford
79. Sinnes K (ed) (2018) *Physics of welding and cutting*. In: *Welding Handbook: Welding and Cutting Science and Technology*, 10th edn, vol 1. American Welding Society, Miami, pp 52–86

80. Kou S (2020) *Welding metallurgy*, 3rd edn. John Wiley & Sons, Hoboken
81. Lancaster JF (1999) *Metallurgy of welding*, 6th edn. Woodhead Publishing, Cambridge
82. EN 1011-2:2001 (2001) *Welding — Recommendations for welding of metallic materials — Part 2: Arc welding of ferritic steels*
83. AWS D1.1/D1.1M:2020 (2020) *Structural welding code — Steel*. American Welding Society, Miami
84. Shafi SM, Fatima A, Hendrickson NV (2025) Characterizing surface waviness of aluminum alloy: An approach to minimize post-processing in wire arc additive manufacturing (WAAM) production. *J Manuf Mater Process* 9(11):347. doi: 10.3390/jmmp9110347.
85. Mishra SK, R SP, Jose SSS, Upadhyay RK (2025) Wire arc additive manufacturing: materials, processes and its constraints. *Mater Manuf Process* 40(6):723–740. doi: 10.1080/10426914.2025.2469525.
86. Banerjee A et al (2026) Near-net-shape wire-arc additive manufacturing (WAAM) of bimetallic P22 steel and Inconel 625: microstructure–property correlations. *Prog Addit Manuf* 11(4):3125–3135. doi: 10.1007/s40964-025-01511-9.
87. Li R et al (2024) Simulation of residual stress and distortion evolution in dual-robot collaborative wire-arc additive manufactured Al-Cu alloys. *Virtual Phys Prototyp* 19(1):e2409390. doi: 10.1080/17452759.2024.2409390.
88. Rosenthal D (1946) The theory of moving sources of heat and its application to metal treatments. *Trans ASME* 68(8):849–866. doi: 10.1115/1.4018624.
89. Keeley W, Turner R, Mitchell B, Warnken N (2025) A development of the Rosenthal equation for predicting thermal profiles during additive manufacturing. *Thermo* 5(2):16. doi: 10.3390/thermo5020016.
90. Flemings MC (1974) *Solidification processing*. McGraw-Hill, New York
91. Kurz W, Fisher DJ (1998) *Fundamentals of solidification*, 4th edn. Trans Tech Publications, Aedermannsdorf
92. Greer AL, Bunn AM, Tronche A, Evans PV, Bristow DJ (2000) Modelling of inoculation of metallic melts: application to grain refinement of aluminium by Al–Ti–B. *Acta Mater* 48(11):2823–2835. doi: 10.1016/S1359-6454(00)00094-X.
93. Walbrühl M, Linder D, Ågren J, Borgenstam A (2017) Modelling of solid solution strengthening in multicomponent alloys. *Mater Sci Eng A* 700:301–311. doi: 10.1016/j.msea.2017.06.001.
94. Ondicho I, Alunda B, Kamau K (2023) Solid solution strengthening in high-entropy alloys. In: *High entropy materials - microstructures and properties*. IntechOpen, London, ch 4. doi: 10.5772/intechopen.107255.
95. Zhang HL et al (2022) Solid solution strengthening of high-entropy alloys from first-principles study. *J Mater Sci Technol* 121:105–116. doi: 10.1016/j.jmst.2021.11.076.
96. Wu Z, Gao Y, Bei H (2016) Thermal activation mechanisms and Labusch-type strengthening analysis for a family of high-entropy and equiatomic solid-solution alloys. *Acta Mater* 120:108–119. doi: 10.1016/j.actamat.2016.08.047.
97. Wang S et al (2023) Modeling the effect of precipitation spatial geometry and size distribution on the yield strength of aluminum alloys. *Acta Mech* 234(9):4323–4342. doi: 10.1007/s00707-023-03608-0.
98. Myhr OR, Grong Ø (2000) A model for predicting the age-hardening behavior of Al-Mg-Si alloys. *Acta Mater* 48(7):1605–1615. doi: 10.1016/S1359-6454(99)00435-X.
99. Deschamps A, Bréchet Y (1998) Influence of pre-deformation and aging of an Al-Zn-Mg alloy-II. Modeling of precipitation kinetics and yield stress. *Acta Mater* 47(1):293–305. doi: 10.1016/S1359-6454(98)00293-6.
100. Körner C, Markl M, Koepf JA (2020) Modeling and simulation of microstructure evolution for additive manufacturing of metals: A critical review. *Metall Mater Trans A* 51(10):4970–4992. doi: 10.1007/s11661-020-05946-0.
101. Deschamps A, Bréchet Y (1998) Influence of predeformation and ageing of an Al-Zn-Mg alloy—II. Modeling of precipitation kinetics and yield stress. *Acta Mater* 47(1):293–305. doi: 10.1016/S1359-6454(98)00293-6.

102. Kampmann R, Wagner R (1984) Kinetics of phase separation in solid solutions—a computer simulation via a systematic integration of Allen-Cahn/Cahn-Hilliard-type equations. *Mater Sci Technol* 15:521–526
103. Zener C (1949) Theory of growth of spherical precipitates from solid solution. *J Appl Phys* 20(10):950–953. doi: 10.1063/1.1698258.
104. Robson JD (2004) Microstructure modeling of 7xxx aluminum alloys during welding. *Mater Sci Eng A* 382(1–2):225–234. doi: 10.1016/j.msea.2004.05.024.
105. Simar A et al (2012) Integrated modeling of friction stir welding in 6xxx series Al alloys: Process, microstructure and properties. *Prog Mater Sci* 57(1):95–132. doi: 10.1016/j.pmatsci.2011.05.003.
106. Gideon Ganesh M et al (2023) Investigation on mechanical properties of ER70S-6 copper-coated steel wire sample produced by wire arc additive manufacturing (WAAM). In: *International Conference on Trends in Automotive Parts Systems and Applications*, Kuniamuthur, Coimbatore, India, 21 Dec 2023. doi: 10.4271/2023-01-5105.
107. Oñate A et al (2026) Multiscale analysis of microstructural evolution and mechanical response in WAAM-GMAW ER70S-6 steel under different deposition conditions. *Int J Adv Manuf Technol*. doi: 10.1007/s00170-026-19013-5.
108. Corpus A (2019) Manipulation of mechanical properties of WAAM deposited ER70S-6 through active cooling. Dissertation, University of Idaho
109. Dekis M, Tawfik M, Egiza M, Dewidar M (2025) Challenges and developments in wire arc additive manufacturing of steel: A review. *Results Eng* 26:104657. doi: 10.1016/j.rineng.2025.104657.
110. Abbaszadeh M, Bol N, Ece Kara O, Sen AA, Yılmaz O (2022) Mechanical behavior and microstructural characterization of wire and arc additive manufacturing of er70s-6 low carbon steel alloy. *J Addit Manuf Technol* 2:2212648. doi: 10.18416/JAMTECH.2212648.
111. Tanwar RS, Bhingole P, Jhavar S (2025) A comprehensive review on wire arc additive manufacturing of inconel superalloys. In: *Advances in materials engineering*. Springer, ch 10, pp 115–128. doi: 10.1007/978-981-97-7114-1_10.