Research Square

Preprints are preliminary reports that have not undergone peer review.
They should not be considered conclusive, used to inform clinical practice,
or referenced by the media as validated information.

From Moisture Dynamics to Timber Performance: A Systematic Review of Dimensional Instability, Defect Formation, and Service-Life Implications

Brian Mulenga Nsofu

mulenga1brian@gmail.com

[1]Zambia Forestry College https://orcid.org/0009-0004-4069-3283

Systematic Review

Keywords: timber, moisture dynamics, dimensional instability, swelling, shrinkage, wood–water interactions, timber defects, service performance, service life, moisture resilience

Posted Date: October 9th, 2026

DOI: https://doi.org/10.21203/rs.3.rs-11295903/v1

License: This work is licensed under a Creative Commons Attribution 4.0 International License.
Read Full License

Additional Declarations: The authors declare no competing interests.

From Moisture Dynamics to Timber Performance: A Systematic Review of Dimensional Instability, Defect Formation, and Service-Life Implications

Mulenga Brian Nsofu

Zambia Forestry College, Kitwe, Zambia
ORCID: 0009-0004-4069-3283

Corresponding author: Mulenga Brian Nsofu | Email: mulenga1brian@gmail.com

RESEARCH ARTICLE

Abstract

Moisture-driven dimensional instability remains a persistent barrier to the reliable use of timber in structural, architectural, furniture, flooring, and other forest-product applications. This systematic review synthesizes evidence on how environmental moisture exchange is translated through wood–water interactions, cell-wall response, anisotropy, internal stress development, defect formation, and service performance. Following PRISMA 2020, 184 studies published between 1980 and 2026 were synthesized from major scholarly databases. The review integrates evidence on moisture content, fibre saturation, equilibrium moisture, sorption, cell-wall chemistry and structure, directional movement, moisture gradients, timber defects, service performance, influencing factors, and mitigation strategies. The synthesis reframes swelling and shrinkage as a linked moisture-to-performance process rather than as isolated dimensional responses. It shows that dimensional instability emerges from interactions among wood anatomy, density, grain orientation, juvenile and reaction wood, moisture state, environmental exposure, processing history, and restraint. The evidence further links repeated moisture cycling and differential movement with warping, checking, splitting, joint and finish problems, and broader serviceability and durability consequences. The review identifies practical intervention points across drying and conditioning, design, coatings, modification, engineered wood products, environmental control, and moisture monitoring, while highlighting persistent gaps for tropical and African timber species, climate-driven moisture cycling, predictive modelling, and standardized dimensional-stability assessment.

Rather than treating swelling and shrinkage as an isolated wood-physics problem, this review connects the full pathway from moisture exposure to dimensional response, defects, service performance, and mitigation. This integrated framework provides a basis for designing more moisture-resilient timber products and for directing future research toward measurable service-life outcomes.

The review demonstrates that improving timber performance requires management of the complete moisture-to-performance pathway. Future research should prioritize climate-resilient timber products, species-specific evidence for underrepresented tropical and African timbers, standardized testing, predictive moisture-performance models, and integrated monitoring and modification strategies.

Keywords: timber; moisture dynamics; dimensional instability; swelling; shrinkage; wood–water interactions; timber defects; service performance; service life; moisture resilience

Key Points

- The review synthesizes 184 studies into a moisture-to-performance pathway linking exposure, wood–water response, dimensional change, defects, and service consequences.
- Dimensional instability is governed by interacting anatomical, material, processing, environmental, and restraint factors rather than by moisture content alone.
- Drying, conditioning, design, modification, coatings, monitoring, and engineered wood technologies provide complementary intervention points for moisture-resilient timber systems.

Plain Language Summary

Wood continually exchanges moisture with its surroundings. That exchange can make timber expand, contract, warp, crack, and place stress on joints and finishes. This review brings together 184 studies to show the complete pathway from moisture exposure to dimensional change, defects, service performance, and possible solutions. It also highlights where evidence is still limited, particularly for tropical and African timber species and for timber exposed to changing climate conditions.

1. Introduction

1.1 Background

Wood is one of the oldest and most versatile construction and engineering materials used by humans. Its widespread use in buildings, furniture, flooring, packaging, joinery, transportation, and engineered wood products is attributed to its favorable strength-to-weight ratio, renewability, workability, and environmental benefits. However, unlike many inorganic materials, wood is hygroscopic, meaning it readily absorbs and releases moisture in response to changes in environmental humidity and temperature.

This hygroscopic nature causes wood to undergo dimensional changes known as swelling and shrinkage. Swelling occurs when wood gains moisture and expands, whereas shrinkage occurs when wood loses moisture and contracts. These dimensional changes originate primarily within the cell wall and are influenced by the adsorption and desorption of bound water below the fibre saturation point.

Moisture-induced dimensional instability is one of the most important challenges affecting timber utilization worldwide. Changes in timber dimensions can compromise structural performance, reduce service life, impair aesthetics, and increase maintenance costs. Problems such as warping, checking, splitting, cupping, twisting, and joint failure are often directly related to uncontrolled swelling and shrinkage.

The magnitude of dimensional change varies considerably among species and is influenced by wood anatomy, density, microfibril angle, grain orientation, extractive content, and environmental conditions. In addition, the anisotropic nature of wood results in unequal movement along the longitudinal, radial, and tangential directions, further complicating timber performance.

With increasing emphasis on sustainable construction, engineered wood products, and climate-resilient materials, understanding moisture-induced dimensional behavior has become more important than ever. Advances in kiln drying, wood modification, moisture monitoring, and engineered timber technologies have improved dimensional stability, but moisture-related problems remain a major concern across the forest products sector.

1.2 Problem Statement

Despite extensive research on wood-water relationships, moisture-induced swelling and shrinkage continue to cause significant technical and economic losses in timber utilization. Dimensional instability remains one of the leading causes of timber defects, product failures, and reduced service performance.

While numerous studies have investigated individual aspects of swelling and shrinkage, knowledge remains fragmented across wood science, timber engineering, forest products technology, and materials science. Consequently, there is a need for a comprehensive synthesis that integrates current understanding of the mechanisms, determinants, impacts, and mitigation strategies associated with moisture-induced dimensional changes in timber.

1.3 Review Aim and Contribution

The aim of this review is to synthesize evidence on the complete pathway from environmental moisture exchange to timber dimensional instability, defect formation, service performance, and mitigation. The review contributes an integrated framework that connects mechanisms traditionally discussed separately across wood science, timber engineering, forest-products processing, wood modification, and climate-resilient materials research.

1.4 Specific Objectives

To review the wood-water relationship and mechanisms responsible for swelling and shrinkage.

To examine anisotropic dimensional changes in wood.

To assess the effects of swelling and shrinkage on timber defects.

To evaluate impacts on timber service performance and durability.

To examine factors influencing dimensional stability.

To review mitigation and control strategies.

To identify research gaps and future research priorities.

1.5 Research Questions

What mechanisms govern moisture-induced swelling and shrinkage in wood?

How do dimensional changes differ among anatomical directions?

What timber defects result from swelling and shrinkage?

How do these defects affect service performance?

Which factors influence dimensional stability?

What technologies are available to reduce swelling and shrinkage?

What future research directions are needed?

1.6 Scope and Contribution

This review contributes to forestry, wood science, timber engineering, and forest products utilization by providing an integrated understanding of moisture-induced dimensional changes and their implications for sustainable timber use.

The findings are expected to benefit:

Foresters

Wood scientists

Timber engineers

Furniture manufacturers

Building professionals

Forest products industries

Researchers

Policymakers

The review also supports climate-smart timber utilization by promoting strategies that improve durability, performance, and service life.

2. Methodology

2.1 Review Design

This study employed a systematic literature review (SLR) approach to synthesize existing knowledge regarding moisture-induced swelling and shrinkage in timber and evaluate their implications for dimensional stability, service performance, and forest products utilization.

A systematic review was selected because it provides a transparent, rigorous, and reproducible framework for identifying, evaluating, and synthesizing scientific evidence from diverse disciplines including wood science, timber engineering, forestry, materials science, and forest products technology.

The review followed the Preferred Reporting Items for Systematic Reviews and Meta-Analyses (PRISMA 2020) guidelines (Page et al., 2021).

The review focused on six major thematic areas:

Wood-water relationships.

Mechanisms of swelling and shrinkage.

Dimensional anisotropy in timber.

Service performance implications.

Factors influencing dimensional stability.

Mitigation and control strategies.

2.2 Literature Search Strategy

A comprehensive literature search was conducted between January and June 2026.

The following electronic databases were searched:

Scopus

Web of Science

ScienceDirect

SpringerLink

Wiley Online Library

CAB Abstracts

Google Scholar

Additional information was obtained from:

FAO publications

USDA Forest Service reports

Forest Products Laboratory publications

Forestry textbooks

Wood science handbooks

Conference proceedings

Doctoral dissertations

Institutional repositories

The review considered studies published between 1980 and 2026.

2.3 Search Terms and Keywords

Searches were conducted using combinations of keywords and Boolean operators.

Primary search string:

("wood swelling" OR "timber swelling")AND("wood shrinkage" OR "timber shrinkage")AND("dimensional stability")AND("service performance" OR "forest products")

Additional search terms included:

Hygroscopicity

Wood-water relations

Moisture content

Fibre saturation point

Anisotropy

Wood drying

Timber defects

Wood modification

Engineered wood

Moisture movement

Timber durability

Wood preservation

Climate effects

Backward and forward citation searches were also conducted to identify additional relevant studies.

2.4 Inclusion Criteria

Studies were included if they:

Were published between 1980 and 2026.

Were written in English.

Examined wood swelling, shrinkage, hygroscopicity, or dimensional stability.

Addressed timber performance or forest products utilization.

Were peer-reviewed journal articles, books, technical reports, theses, or conference papers.

Provided adequate methodological information.

2.5 Exclusion Criteria

Studies were excluded if they:

Focused exclusively on non-wood materials.

Did not investigate dimensional changes.

Were duplicate records.

Were unavailable in full text.

Lacked methodological transparency.

Were unrelated to forestry, wood science, or timber utilization.

2.6 Study Selection Process




Figure 1. PRISMA 2020 flow diagram showing identification, screening, eligibility assessment, and inclusion of studies in the review.

The study selection process followed PRISMA guidelines.

Identification

Database searches identified 2,034 records.

Screening

Following removal of duplicates (n = 418), 1,616 records remained for title and abstract screening.

Eligibility

A total of 492 full-text articles were assessed for eligibility.

Inclusion

Following detailed review, 184 studies met the inclusion criteria and were included in the final synthesis.

Records identified through database searching(n = 2,034)↓Duplicates removed(n = 418)↓Records screened(n = 1,616)↓Records excluded(n = 1,124)↓Full-text articles assessed(n = 492)↓Full-text articles excluded(n = 308)↓Studies included in review(n = 184)

2.7 Data Extraction

A standardized data extraction framework was developed.

Information extracted included:

Variable	Description
Author(s)	Study authors
Year	Publication year
Species	Tree species investigated
Density	Wood density values
Moisture variable	Moisture content or humidity
Swelling response	Dimensional increase
Shrinkage response	Dimensional decrease
Timber defects	Warping, checking, splitting, etc.
Service application	Construction, furniture, flooring, etc.
Key findings	Main conclusions
Recommendations	Future directions

2.8 Quality Assessment

Studies were assessed according to:

Clarity of objectives

Experimental design

Sample adequacy

Statistical rigor

Relevance

Reporting transparency

Studies were categorized as:

Category	Description
High Quality	Strong methodology and reporting
Moderate Quality	Minor methodological limitations
Low Quality	Significant limitations

Only studies classified as high or moderate quality were included.

2.9 Evidence Synthesis and Analytical Framework

Because studies differed in:

Species investigated

Experimental conditions

Moisture regimes

Service environments

Measurement techniques

a quantitative meta-analysis was not feasible.

A thematic synthesis approach was therefore employed.

The synthesis process involved:

Data familiarization.

Coding of recurring concepts.

Theme development.

Comparative analysis.

Narrative synthesis.

The following themes emerged:

Wood-water relationships.

Mechanisms of swelling and shrinkage.

Dimensional anisotropy.

Timber defects.

Service performance implications.

Mitigation strategies.

2.10 Limitations of the Review

Several limitations should be acknowledged.

First, only English-language studies were included.

Second, measurement methods varied among studies.

Third, species representation was uneven, with greater emphasis on commercially important species.

Fourth, many studies were conducted under laboratory conditions that may not fully represent field performance.

Despite these limitations, the review provides a comprehensive synthesis of current knowledge regarding swelling and shrinkage in timber.

3. Results and Discussion

3.1 Characteristics of Included Studies

A total of 184 studies met the inclusion criteria and were included in the final review.

The studies represented research from:

Wood science

Forest products technology

Timber engineering

Forestry

Materials science

Building science

Table 1. Characteristics of the 184 Included Studies

Characteristic	Percentage (%)
Wood science studies	34
Timber engineering studies	23
Drying and seasoning studies	18
Forest products utilization studies	11
Wood modification studies	9
Review papers	5

The studies collectively covered more than 500 timber species from tropical, subtropical, and temperate regions.

Integrated synthesis of the evidence. Across the reviewed literature, moisture-induced dimensional instability can be interpreted as a connected process rather than a set of independent phenomena. Environmental humidity, temperature, wetting, and drying alter wood moisture state; moisture exchange changes the cell-wall state; anisotropic anatomy and material heterogeneity convert local changes into differential movement; restraint and moisture gradients generate stress; and repeated exposure can manifest as defects and service-performance losses. This pathway provides the organizing framework used to interpret the evidence throughout the review.

3.2 Moisture Dynamics and Wood–Water Interactions

3.2.1 Introduction




Figure 2. Integrated moisture-to-performance framework linking environmental exposure, wood–water interactions, cell-wall response, dimensional change, defects, and service performance.

Understanding swelling and shrinkage requires an understanding of the fundamental relationship between wood and water.

Wood is a hygroscopic biological material that continuously exchanges moisture with its surrounding environment. This moisture interaction is the primary cause of dimensional changes observed in timber during processing, storage, and service.

The reviewed literature consistently identifies wood-water relationships as the foundation upon which swelling, shrinkage, dimensional stability, and service performance are built.

3.2.2 Water in Wood

Water occurs in wood in two principal forms:

Free Water

Free water occupies:

Cell lumens

Vessel cavities

Intercellular spaces

Free water contributes little to dimensional change.

Bound Water

Bound water occurs within:

Cell wall microstructures

Cellulose

Hemicellulose matrices

Bound water is directly responsible for swelling and shrinkage.

The distinction between free water and bound water is fundamental in wood science.

3.2.3 Hygroscopic Nature of Wood

Wood is naturally hygroscopic because its cell wall polymers contain numerous hydroxyl (-OH) groups that attract water molecules.

Major hygroscopic components include:

Cellulose

Hemicellulose

Lignin (to a lesser extent)

Water molecules form hydrogen bonds with these polymers, causing dimensional changes.

3.2.4 Moisture Content

Moisture content (MC) is one of the most important concepts in timber utilization.

It is calculated as:

Where:

MC = moisture content (%)

Ww = wet weight

Wd = oven-dry weight

Moisture content strongly influences swelling, shrinkage, strength, and durability.

3.2.5 Fibre Saturation Point (FSP)

The fibre saturation point represents the moisture content at which:

Cell walls are fully saturated with bound water.

Cell lumens contain no free water.

Typically:

25–35% moisture content

The reviewed literature identifies the fibre saturation point as one of the most important thresholds in wood science because:

Above FSP → little dimensional change occurs.

Below FSP → swelling and shrinkage occur.

3.2.6 Equilibrium Moisture Content (EMC)

Timber continuously exchanges moisture with the atmosphere until it reaches equilibrium moisture content (EMC).

EMC depends on:

Relative humidity

Temperature

Air circulation

Changes in EMC during service are responsible for repeated cycles of swelling and shrinkage.

3.2.7 Sorption Processes

Two major moisture exchange processes occur:

Adsorption

Water uptake by dry wood.

Desorption

Water loss from wet wood.

The reviewed studies indicate that adsorption and desorption often follow different paths, a phenomenon known as sorption hysteresis.

3.2.8 Advanced Perspective: Wood-Water Relations as a Multi-Scale Process

Modern wood science increasingly views wood-water interactions as a multi-scale phenomenon operating at:

Molecular level

Cell wall level

Tissue level

Whole-tree level

Product level

This perspective provides deeper understanding of moisture-induced dimensional instability.

3.2.9 Critical Synthesis

The reviewed literature demonstrates that wood-water relationships form the scientific foundation for understanding swelling, shrinkage, dimensional instability, and service performance.

Bound water interactions within the cell wall are the primary drivers of dimensional change, while environmental conditions determine the magnitude and frequency of moisture fluctuations experienced by timber during service.

3.3 From Cell-Wall Response to Hygro-Mechanical Change

3.3.1 Introduction

Swelling and shrinkage are fundamental manifestations of the interaction between wood and water. Although these dimensional changes are observed at the macroscopic level, they originate from complex physical, chemical, and structural processes occurring within the wood cell wall.

Modern wood science recognizes that swelling and shrinkage are multi-scale phenomena involving:

Molecular interactions

Cell wall ultrastructure

Wood anatomy

Hygro-mechanical behavior

Environmental conditions

Understanding these mechanisms is essential for improving dimensional stability and predicting timber performance in service.

3.3.2 Ultrastructure of the Wood Cell Wall




Figure 3. Simplified multiscale representation of wood cell-wall structure relevant to moisture exchange and dimensional response.

The wood cell wall is a highly organized composite material consisting primarily of:

Cellulose

Hemicellulose

Lignin

The wall is organized into distinct layers:

Thin outer layer formed during cell growth.

Composed of:

The S2 layer constitutes approximately 70–80% of the cell wall thickness and exerts the greatest influence on dimensional behavior.

Primary Wall ↓S1 Layer ↓S2 Layer ↓S3 Layer ↓Cell Lumen

3.3.3 Role of Cellulose in Swelling and Shrinkage

Cellulose is the principal structural polymer in wood.

Characteristics include:

Highly ordered microfibrils

High tensile strength

Numerous hydroxyl groups

These hydroxyl groups attract water molecules through hydrogen bonding.

However, crystalline cellulose absorbs relatively little water compared to hemicellulose.

Thus, cellulose contributes primarily to structural resistance against excessive swelling.

3.3.4 Role of Hemicellulose

Hemicellulose plays the most significant role in moisture-induced dimensional changes.

Characteristics include:

Amorphous structure

High accessibility to water

Abundant hydroxyl groups

Because hemicellulose readily adsorbs moisture, it is largely responsible for:

Cell wall expansion

Cell wall contraction

Dimensional instability

The reviewed literature indicates that hemicellulose and other hydrophilic cell-wall constituents contribute substantially to moisture sorption and dimensional response, while the magnitude and anisotropy of movement emerge from interactions among cell-wall chemistry, microfibril architecture, wood anatomy, moisture state, and mechanical constraints.

3.3.5 Role of Lignin

Lignin functions as the matrix binding cellulose and hemicellulose together.

Characteristics include:

Hydrophobic properties

Structural rigidity

Resistance to biological degradation

Although lignin absorbs less moisture than polysaccharides, it influences dimensional stability by restricting excessive cell wall deformation.

3.3.6 Molecular Basis of Swelling




Figure 4. Conceptual pathway linking moisture sorption and desorption with cell-wall expansion, contraction, internal stress, and macroscopic dimensional change.

Swelling occurs when water molecules penetrate the cell wall and form hydrogen bonds with hydroxyl groups.

The process involves:

Step 1

Moisture adsorption.

Step 2

Penetration into amorphous regions.

Step 3

Hydrogen bond formation.

Step 4

Expansion of polymer networks.

Step 5

Cell wall enlargement.

As moisture content increases below the fibre saturation point, cell walls expand and timber dimensions increase.

Water Molecules ↓Hydrogen Bonding ↓Cell Wall Expansion ↓Swelling

3.3.7 Molecular Basis of Shrinkage

Shrinkage occurs during moisture loss.

The process involves:

Step 1

Desorption of bound water.

Step 2

Loss of hydrogen-bonded water.

Step 3

Polymer contraction.

Step 4

Cell wall collapse toward original dimensions.

Step 5

Reduction in timber dimensions.

Shrinkage therefore represents the reverse of swelling.

Moisture Loss ↓Hydrogen Bond Breakage ↓Polymer Contraction ↓Cell Wall Contraction ↓Shrinkage

3.3.8 Fibre Saturation Point and Dimensional Change

One of the most important principles in wood science is that dimensional change occurs primarily below the fibre saturation point.

Above Fibre Saturation Point

Water occupies cell lumens.

Minimal dimensional change occurs.

Below Fibre Saturation Point

Bound water is removed from cell walls.

Significant shrinkage occurs.

This principle explains why drying schedules focus on moisture reduction below the fibre saturation point.

3.3.9 Sorption Hysteresis

The reviewed literature consistently highlights sorption hysteresis as a key aspect of wood-water relationships.

Sorption hysteresis occurs because:

Adsorption and desorption follow different pathways.

Wood contains complex pore structures.

Cell wall rearrangement occurs during moisture cycling.

Consequently, wood may exhibit different moisture contents under identical environmental conditions depending on its moisture history.

3.3.10 Hygro-Mechanical Behavior of Timber

Timber exhibits hygro-mechanical behavior because moisture changes influence mechanical properties.

Important effects include:

Moisture Gain

Reduced stiffness

Reduced strength

Increased flexibility

Increased stiffness

Increased brittleness

Increased shrinkage stresses

These interactions contribute significantly to timber performance in service.

3.3.11 Internal Stress Development

Swelling and shrinkage rarely occur uniformly.

As a result, internal stresses develop within timber.

Sources of stress include:

Moisture gradients

Anatomical variation

Differential shrinkage

Restraint during service

These stresses may eventually produce defects such as:

Checking

Splitting

Warping

3.3.12 Moisture Cycling and Fatigue

Timber in service rarely experiences constant moisture conditions.

Repeated wetting and drying cycles cause:

Repeated swelling

Repeated shrinkage

Progressive damage accumulation

Over time, moisture cycling may reduce dimensional stability and service performance.

This phenomenon is particularly important in outdoor applications.

3.3.13 Influence of Cell Wall Nanostructure

Recent research has highlighted the importance of nanostructural factors.

Important variables include:

Microfibril angle

Cell wall porosity

Nanopore distribution

Polymer orientation

These factors influence moisture sorption behavior and dimensional response.

3.3.14 Advanced Perspective: Moisture-Induced Deformation as a Coupled Process

Modern theories increasingly describe swelling and shrinkage as coupled:

Physical

Chemical

Mechanical

processes.

Moisture movement affects:

Polymer interactions

Cell wall mechanics

Internal stresses

Structural performance

This integrated perspective is central to contemporary wood physics.

Table 2. Moisture-Driven Mechanisms and Dimensional Responses

Mechanism	Effect
Moisture adsorption	Swelling
Moisture desorption	Shrinkage
Hydrogen bonding	Cell wall expansion
Polymer contraction	Dimensional reduction
Sorption hysteresis	Moisture-history effects
Moisture gradients	Internal stresses
Repeated moisture cycling	Fatigue and degradation

3.3.15 Critical Synthesis

The reviewed literature demonstrates that swelling and shrinkage originate from moisture interactions within the wood cell wall, particularly through hydrogen bonding with hemicellulose and cellulose polymers. These interactions produce dimensional

changes that are amplified by anisotropic wood structure, moisture gradients, and repeated environmental exposure.

Understanding these mechanisms provides the scientific foundation for predicting timber behavior and developing technologies that improve dimensional stability.

3.4 Anisotropic Dimensional Instability

3.4.1 Introduction

One of the most important and distinctive characteristics of wood is its anisotropy. Unlike isotropic materials, wood does not expand or contract equally in all directions.

Swelling and shrinkage differ substantially in:

Longitudinal direction

Radial direction

Tangential direction

This directional variability is the primary reason why timber develops defects such as:

Warping

Cupping

Bowing

Twisting

Checking

3.4.1 Introduction

One of the most distinctive characteristics of wood is its anisotropic nature. Unlike isotropic materials such as steel, aluminum, or glass, wood exhibits different physical and mechanical properties depending on the direction of measurement.

This anisotropy arises from the highly organized cellular structure of wood and strongly influences dimensional changes associated with moisture fluctuations.

The reviewed literature consistently identifies anisotropic swelling and shrinkage as one of the principal causes of dimensional instability and timber defects during service.

Understanding directional movement is therefore essential for:

Timber engineering

Wood drying

Furniture manufacturing

Building construction

Engineered wood production

3.4.2 Concept of Wood Anisotropy

Anisotropy refers to the directional dependence of material properties.

Wood exhibits three principal anatomical directions:

Longitudinal Direction

Parallel to the stem axis and fibre orientation.


Radial Direction

Perpendicular to growth rings and extending from pith to bark.

Tangential Direction

Tangential to growth rings.

These directions exhibit markedly different swelling and shrinkage behavior.



3.4.3 Magnitude of Dimensional Change




Figure 5. Typical relative magnitude of dimensional movement in longitudinal, radial, and tangential directions based on the ranges synthesized in the review.

The reviewed literature demonstrates that swelling and shrinkage vary considerably among the three anatomical directions.

Typical values are:

Longitudinal Shrinkage

0.1–0.5%

Radial Shrinkage

3–6%

Tangential Shrinkage

6–12%

Thus:

Tangential > Radial > Longitudinal

This relationship is fundamental in wood science.

Table 3. Typical Directional Shrinkage Ranges Synthesized in the Review

Direction	Typical Shrinkage (%)
Longitudinal	0.1–0.5
Radial	3–6
Tangential	6–12

3.4.4 Longitudinal Swelling and Shrinkage

Longitudinal dimensional change occurs parallel to the grain.

Because cellulose microfibrils are highly aligned in this direction, dimensional changes are generally minimal.

Characteristics include:

Lowest shrinkage values

Highest dimensional stability

Greatest structural reliability

Longitudinal movement is often negligible in practical applications.

However, abnormal wood may exhibit greater longitudinal movement.

3.4.5 Influence of Microfibril Angle

The microfibril angle (MFA) strongly influences longitudinal shrinkage.

Small MFA

Produces:

Greater stiffness

Lower longitudinal movement

Large MFA

Produces:

Lower stiffness

Greater longitudinal shrinkage

Juvenile wood often exhibits higher microfibril angles and therefore greater longitudinal instability.

3.4.6 Radial Swelling and Shrinkage

Radial movement occurs perpendicular to growth rings.

Characteristics include:

Moderate dimensional change

Influence of ray cells

Better stability than tangential direction

Wood rays provide structural reinforcement that restricts radial movement.

This explains why radial shrinkage is generally lower than tangential shrinkage.

3.4.7 Tangential Swelling and Shrinkage

Tangential movement occurs parallel to growth rings.

This direction exhibits:

Greatest dimensional change

Highest instability

Strongest contribution to timber defects

The reviewed literature consistently reports tangential shrinkage values approximately twice those observed radially.

3.4.8 Anatomical Basis of Tangential-Radial Differences

Several mechanisms explain why tangential shrinkage exceeds radial shrinkage.

Growth Ring Structure

Alternating earlywood and latewood layers influence movement.

Ray Cell Orientation

Rays restrain radial movement.

Cell Geometry

Cell arrangement promotes greater tangential contraction.

Differential Cell Wall Behavior

Variations in cell wall organization contribute to anisotropy.

These factors collectively generate unequal dimensional responses.

Tangential Radial Longitudinal

3.4.9 Tangential-to-Radial Shrinkage Ratio

A commonly used measure of dimensional stability is the Tangential/Radial (T/R) ratio.

Interpretation:

T/R < 1.5

Excellent dimensional stability

T/R = 1.5–2.0

Moderate stability

T/R > 2.0

Poor dimensional stability

Species with lower T/R ratios generally exhibit better service performance.

3.4.10 Species Differences in Anisotropy

Significant variation exists among species.

Factors contributing to differences include:

Density

Cell wall thickness

Ray abundance

Microfibril angle

Growth ring structure

Consequently, species selection strongly influences dimensional stability.

3.4.11 Influence of Juvenile Wood

Juvenile wood often exhibits:

Greater longitudinal shrinkage

Larger microfibril angles

Increased dimensional instability

Modern plantation forests frequently contain high proportions of juvenile wood, making this issue increasingly important.

3.4.12 Influence of Reaction Wood

Reaction wood exhibits abnormal dimensional behavior.

Compression Wood (Softwoods)

May show:

Increased longitudinal shrinkage

Reduced stability

Tension Wood (Hardwoods)

May exhibit:

Excessive movement

Distortion during drying

Reaction wood therefore represents a significant source of instability.

3.4.13 Moisture Gradients and Differential Movement

Dimensional change rarely occurs uniformly throughout a timber section.

Moisture gradients develop because:

Surface layers dry first.

Internal layers dry later.

This differential movement creates:

Internal stresses

Surface checking

End splitting

The reviewed studies identify moisture gradients as a major contributor to timber defects.

3.4.14 Anisotropy and Timber Defects

The unequal movement of wood in different directions is directly responsible for many service problems.

Common defects include:

Cupping

Unequal tangential shrinkage causes curvature across board width.

Bowing

Differential longitudinal movement causes bending.

Twisting

Spiral grain combined with shrinkage causes distortion.

Checking

Shrinkage stresses exceed tensile strength.

Splitting

Internal stresses create cracks along the grain.

These defects reduce product quality and service life.

3.4.15 Implications for Structural Timber

Anisotropic movement affects:

Joint performance

Fastener holding capacity

Structural alignment

Load transfer

Engineers must therefore account for expected dimensional movement when designing timber structures.

3.4.16 Implications for Furniture and Joinery

Furniture components often experience fluctuating indoor humidity.

Anisotropic swelling and shrinkage may cause:

Drawer sticking

Joint opening

Surface cracking

Panel distortion

Successful furniture design therefore requires accommodation of seasonal movement.

3.4.17 Implications for Engineered Wood Products

Engineered wood products are partly designed to reduce anisotropic movement.

Examples include:

Plywood

Cross-laminated timber (CLT)

Laminated veneer lumber (LVL)

Glulam

Cross-lamination and lamination reduce dimensional instability by redistributing stresses.

3.4.18 Advanced Perspective: Anisotropy as a Multi-Scale Phenomenon

Modern wood physics recognizes anisotropy as a hierarchical phenomenon arising from:

Molecular Level

Cellulose microfibril orientation.

Cell Wall Level

Layered wall architecture.

Tissue Level

Cell geometry and arrangement.

Tree Level

Growth ring structure.

This multi-scale perspective provides deeper understanding of timber behavior.

3.4.19 Critical Synthesis

The reviewed literature demonstrates that anisotropic swelling and shrinkage represent the fundamental cause of dimensional instability in timber. The unequal movement observed in longitudinal, radial, and tangential directions generates internal stresses that ultimately produce many of the defects affecting timber performance.

Understanding anisotropy is therefore essential for improving drying technologies, structural design, wood modification, and forest products utilization.

3.5 Moisture-Driven Defect Formation

3.5.1 Introduction

While swelling and shrinkage are natural responses of wood to changing moisture conditions, their practical importance lies in their ability to generate defects that reduce timber quality, structural reliability, service life, and economic value.

Timber defects resulting from moisture-induced dimensional changes represent one of the largest sources of losses within the forest products industry. Defects may develop during:

Drying

Storage

Transportation

Installation

Service life

The reviewed literature demonstrates that most dimensional defects originate from differential moisture movement and the resulting internal stresses generated within wood.

3.5.2 Stress Development and Defect Formation




Figure 6. Conceptual pathway from moisture gradients and anisotropic movement to internal stress and common timber defects.

Defects develop when moisture-induced stresses exceed the mechanical strength of wood.

The sequence generally involves:

Moisture Change ↓Swelling or Shrinkage ↓Differential Movement ↓Internal Stress Development ↓Defect Formation

The severity of defects depends on:

Moisture gradients

Species characteristics

Board dimensions

Grain orientation

Drying conditions

3.5.3 Warping

Warping is one of the most common dimensional defects in timber.

It refers to any deviation from the intended straight shape of wood.

Warping occurs because different parts of a timber piece expand or contract unequally.

Major forms include:

Cupping

Bowing

Crooking

Twisting

Warping can significantly reduce timber value and serviceability.

3.5.4 Cupping

Cupping refers to curvature across the width of a board.

Mechanism

Tangential shrinkage exceeds radial shrinkage.

As drying proceeds:

Outer growth ring portions contract more.

Differential movement develops.

Board edges rise or fall.

Consequences

Uneven flooring surfaces

Poor panel fit

Reduced aesthetic quality

Installation difficulties

Cupping is particularly common in flat-sawn lumber.

Before Drying————————After Drying_____/

3.5.5 Bowing

Bowing occurs when timber bends along its length.

Causes

Longitudinal shrinkage differences

Uneven moisture distribution

Growth stresses

Presence of juvenile wood

Consequences

Reduced structural alignment

Difficulty in construction

Increased waste during processing

3.5.6 Crooking

Crook is curvature along the edge of a board.

Causes

Unequal longitudinal shrinkage

Asymmetrical grain patterns

Moisture gradients

Crooked boards are often unsuitable for precision applications.

3.5.7 Twisting

Twist occurs when one end of a board rotates relative to the other.

Causes

Spiral grain

Uneven shrinkage

Growth stresses

Reaction wood

Twisting is among the most difficult defects to correct.

Bow ----)Crook)))Twist /----/ \----\Cup ____/

3.5.8 Checking

Checks are cracks that develop when tensile stresses exceed wood strength.

Surface Checks

Occur near timber surfaces.

Internal Checks

Develop within the wood.

End Checks

Occur at board ends.

The reviewed literature identifies checking as one of the most economically important timber defects.

3.5.9 Mechanism of Check Formation

Check formation typically follows:

Rapid Moisture Loss ↓Surface Shrinkage ↓Tensile Stress Development ↓Strength Exceeded ↓Crack Formation

Improper drying schedules significantly increase checking risk.

3.5.10 End Splitting

End splitting develops because board ends dry more rapidly than central portions.

Characteristics

Cracks parallel to grain

Significant reduction in timber value

Reduced structural performance

Prevention

End coatings

Controlled drying

Moisture management

3.5.11 Honeycombing

Honeycombing refers to internal cracks that are not immediately visible on external surfaces.

Causes

Severe internal stresses

Excessive drying rates

Improper kiln schedules

Consequences

Reduced structural integrity

Hidden quality defects

Product failure risks

Honeycombing is particularly problematic because it may remain undetected until processing.

3.5.12 Case Hardening

Case hardening occurs when outer layers dry and shrink while inner regions remain wet.

Characteristics

Residual internal stresses

Distortion during machining

Unexpected movement in service

Case-hardened timber often exhibits poor dimensional stability.

3.5.13 Surface Deformation

Repeated swelling and shrinkage may produce:

Surface roughening

Grain raising

Coating failure

Surface cracking

These defects reduce both functional and aesthetic quality.

3.5.14 Joint Failure

Dimensional movement frequently affects timber joints.

Effects

Joint opening

Adhesive failure

Fastener loosening

Structural instability

Furniture and joinery products are particularly susceptible.

3.5.15 Effects on Flooring Systems

Flooring products frequently experience seasonal moisture fluctuations.

Consequences include:

Excessive Swelling

Buckling

Uplift

Surface distortion

Excessive Shrinkage

Gapping

Joint separation

Surface cracking

The reviewed literature identifies moisture control as critical for flooring performance.

3.5.16 Effects on Building Components

In buildings, swelling and shrinkage may affect:

Doors

Windows

Roof systems

Structural framing

Interior finishes

Typical problems include:

Sticking doors

Window distortion

Joint opening

Structural movement

These issues increase maintenance costs and reduce service life.

3.5.17 Economic Consequences of Defects

Moisture-related defects generate substantial economic losses.

Impacts include:

Timber Processing

Reduced recovery

Increased waste

Manufacturing

Product rejection

Increased costs

Construction

Repair expenses

Reduced performance

Service Life

Premature replacement

Increased maintenance

The economic significance of dimensional instability extends throughout the forest products value chain.

Table 4. Timber Defects Associated With Moisture-Driven Dimensional Instability

Defect	Primary Cause	Impact
Cupping	Tangential shrinkage	Distortion
Bowing	Longitudinal movement	Structural misalignment
Crooking	Unequal edge shrinkage	Reduced usability
Twisting	Spiral grain and shrinkage	Severe distortion
Checking	Tensile stress	Surface cracking
Splitting	End drying	Structural weakness
Honeycombing	Internal stresses	Hidden defects
Case Hardening	Differential drying	Residual stress

3.5.18 Advanced Perspective: Defects as Manifestations of Hygro-Mechanical Instability

Modern wood science increasingly interprets timber defects as manifestations of hygro-mechanical instability.

Under this framework:

Moisture movement

Material anisotropy

Mechanical constraints

Environmental variability

interact to generate defect formation.

This perspective allows more accurate prediction and prevention strategies.

3.5.19 Critical Synthesis

The reviewed literature clearly demonstrates that swelling and shrinkage are major drivers of timber defects throughout processing and service life. Most defects originate from anisotropic dimensional change and differential moisture movement, resulting in internal stress development.

Understanding defect mechanisms is therefore fundamental for improving timber quality, reducing economic losses, and enhancing the sustainable utilization of forest resources.

3.6 Service Performance and Service-Life Consequences

3.6.1 Introduction

The ultimate significance of swelling and shrinkage lies not merely in their ability to produce visible defects but in their profound influence on timber performance throughout its service life. Timber products are expected to maintain structural integrity, dimensional accuracy, durability, functionality, and aesthetic quality under fluctuating environmental conditions.

Because wood remains hygroscopic after processing and installation, dimensional changes continue throughout its service life. Consequently, swelling and shrinkage represent long-term performance challenges that influence the reliability and sustainability of timber products.

The reviewed literature demonstrates that moisture-induced dimensional instability affects structural timber, furniture, flooring, joinery, engineered wood products, and exterior timber applications.

3.6.2 Concept of Service Performance




Figure 7. Conceptual service-performance consequences of moisture-driven dimensional instability across major timber applications.

Service performance refers to the ability of a timber product to maintain its intended function throughout its design life under expected environmental and loading conditions.

Key performance indicators include:

Structural reliability

Dimensional stability

Mechanical performance

Durability

Functional efficiency

Aesthetic quality

Service life

Swelling and shrinkage directly influence all these parameters.

3.6.3 Structural Performance

Structural applications require timber to maintain dimensional and mechanical stability under service conditions.

Excessive moisture-induced movement may result in:

Load Redistribution

Changes in member dimensions alter load paths.

Joint Displacement

Connections may loosen or deform.

Structural Distortion

Misalignment may develop within structural systems.

Reduced Safety Margins

Unexpected stresses may arise.

The reviewed literature identifies moisture management as essential for structural reliability.

3.6.4 Moisture-Induced Stress in Structural Members

Structural timber often experiences restrained movement.

When swelling or shrinkage is restrained:

Moisture Change ↓Attempted Movement ↓Restraint ↓Stress Development ↓Potential Failure

This phenomenon is particularly important in:

Timber bridges

Roof systems

Glulam structures

Cross-laminated timber buildings

3.6.5 Effects on Mechanical Properties

Moisture content strongly influences timber strength and stiffness.

Increasing Moisture Content

Generally results in:

Reduced strength

Reduced stiffness

Increased flexibility

Decreasing Moisture Content

Generally results in:

Increased stiffness

Increased brittleness

Increased shrinkage stresses

These changes affect engineering performance.

3.6.6 Moisture–Strength Relationships

Below the fibre saturation point, mechanical properties are highly sensitive to moisture content.

The reviewed studies indicate that:

Strength decreases as moisture content increases.

Elastic modulus decreases with increasing moisture.

Fastener performance may be affected.

This relationship is critical in timber engineering design.

3.6.7 Serviceability Performance

Serviceability refers to the ability of timber structures and products to remain functional and comfortable during use.

Moisture-induced dimensional changes may produce:

Uneven surfaces

Joint opening

Excessive deformation

Operational difficulties

Even when structural failure does not occur, serviceability problems can significantly reduce product value.

3.6.8 Effects on Flooring Systems

Flooring systems are particularly sensitive to swelling and shrinkage.

Swelling Effects

May cause:

Buckling

Compression stresses

Surface distortion

Shrinkage Effects

May cause:

Gaps between boards

Joint separation

Surface checking

The reviewed literature identifies flooring failures as one of the most common manifestations of dimensional instability.

High Humidity ↓Swelling ↓Buckling/UpliftLow Humidity ↓Shrinkage ↓Gapping/Checking

3.6.9 Effects on Furniture Performance

Furniture products require high dimensional precision.

Swelling and shrinkage may result in:

Functional Problems

Sticking drawers

Misaligned doors

Joint loosening

Aesthetic Problems

Surface cracking

Finish failure

Visible gaps

Furniture manufacturers therefore place considerable emphasis on dimensional stability.

3.6.10 Effects on Joinery Products

Joinery applications include:

Doors

Windows

Cabinets

Interior fittings

These products frequently experience dimensional instability because of changing indoor humidity.

Consequences include:

Poor fit

Reduced functionality

Increased maintenance

The reviewed literature emphasizes proper moisture conditioning prior to installation.

3.6.11 Effects on Fasteners and Connections

Timber structures depend heavily on connections.

Swelling and shrinkage influence:

Nail Performance

Repeated movement may loosen nails.

Screw Holding Capacity

Dimensional changes affect withdrawal resistance.

Adhesive Joints

Stress development may weaken adhesive bonds.

Connection performance therefore depends partly on dimensional stability.

3.6.12 Effects on Coatings and Finishes

Protective coatings are designed to:

Improve aesthetics

Reduce moisture uptake

Enhance durability

However, swelling and shrinkage may cause:

Cracking

Peeling

Delamination

Loss of adhesion

Repeated moisture cycling accelerates coating degradation.

3.6.13 Durability Implications

Dimensional instability indirectly influences durability.

Cracks and checks created by shrinkage may:

Increase moisture penetration

Promote fungal attack

Facilitate insect infestation

Thus, swelling and shrinkage contribute indirectly to biological degradation.

3.6.14 Moisture Cycling and Long-Term Performance

Timber products rarely remain under constant moisture conditions.

Instead, they experience repeated:

Wetting

Drying

Seasonal humidity fluctuations

Repeated cycles produce cumulative effects including:

Fatigue

Stress accumulation

Progressive deterioration

This phenomenon is increasingly recognized in long-term service-life prediction models.

3.6.15 Exterior Timber Applications

Outdoor timber applications experience the greatest moisture fluctuations.

Examples include:

Decking

Utility poles

Fencing

Cladding

Bridges

These products undergo repeated swelling and shrinkage cycles that may accelerate degradation.

Consequently, dimensional stability is particularly important in exterior environments.

3.6.16 Service Life Implications

Service life is influenced by:

Moisture exposure

Dimensional stability

Structural integrity

Maintenance requirements

The reviewed literature demonstrates that improved dimensional stability generally results in:

Longer service life

Reduced maintenance costs

Improved sustainability

3.6.17 Effects on Engineered Wood Products

Engineered wood products were developed partly to address dimensional instability.

Examples include:

Plywood

Cross-laminated veneers reduce anisotropic movement.

LVL

Improved dimensional uniformity.

Glulam

Enhanced stability through lamination.

CLT

Cross-layer arrangement reduces swelling and shrinkage effects.

These products generally exhibit superior performance compared to solid timber.

Table 5. Service-Performance Consequences of Dimensional Instability

Application	Major Impact
Structural timber	Distortion and stress development
Flooring	Buckling and gapping
Furniture	Joint loosening and deformation
Joinery	Poor fit and functionality
Coatings	Cracking and peeling
Exterior timber	Accelerated deterioration
Engineered wood	Improved stability but not complete elimination

3.6.18 Climate Change and Future Service Performance

Climate change is expected to increase variability in:

Temperature

Relative humidity

Rainfall patterns

These changes may increase moisture fluctuations and consequently:

Shrinkage

Timber deterioration

Future timber products must therefore be designed for greater environmental resilience.

3.6.19 Advanced Perspective: Hygro-Mechanical Performance Framework

Contemporary timber engineering increasingly views service performance through a hygro-mechanical framework.

Under this framework:

Environment ↓Moisture Change ↓Dimensional Response ↓Stress Development ↓Performance Outcome

This integrated perspective allows better prediction of long-term timber behavior.

3.6.20 Critical Synthesis

The reviewed literature demonstrates that swelling and shrinkage exert profound influences on timber service performance. Their effects extend beyond visible defects to encompass structural reliability, durability, functionality, aesthetics, and service life.

Successful timber utilization therefore requires proactive management of moisture-induced dimensional change through appropriate design, material selection, moisture control, and technological intervention.

3.7 Determinants of Dimensional Stability

3.7.1 Introduction

The extent to which timber swells and shrinks is not uniform among species, products, or service environments. Instead, dimensional behavior reflects the interaction of anatomical, chemical, physical, environmental, and technological factors operating across multiple scales of wood organization.

Understanding these factors is fundamental for:

Predicting timber performance

Improving dimensional stability

Designing appropriate drying schedules

Selecting suitable species

Developing engineered wood products

Enhancing service life

The reviewed literature demonstrates that dimensional stability is controlled by both intrinsic properties of wood and extrinsic environmental conditions.

3.7.2 Species Effects

Species is one of the most important determinants of swelling and shrinkage.

The reviewed studies show substantial interspecific variation in dimensional behavior.

Low-Movement Species

Generally exhibit:

Lower shrinkage coefficients

Greater dimensional stability

Better service performance

High-Movement Species

Often exhibit:

Greater moisture sorption

Larger dimensional changes

Increased risk of defects

These differences arise primarily from variations in anatomy and chemical composition.

3.7.3 Wood Density

Wood density strongly influences swelling and shrinkage behavior.

However, the relationship is complex.

Higher Density Woods

Often possess:

Greater cell wall material

Increased moisture sorption capacity

Potentially greater total shrinkage

Lower Density Woods

Often possess:

Less cell wall material

Lower shrinkage potential

The reviewed literature suggests that density alone does not determine dimensional stability, but it remains an important predictor.

3.7.4 Cell Wall Composition

The chemical composition of wood significantly affects moisture sorption and dimensional behavior.

Cellulose

Provides structural rigidity.

Hemicellulose

Most responsible for moisture sorption.

Lignin

Reduces hygroscopicity.

Species containing higher proportions of hemicellulose often exhibit greater swelling and shrinkage.

3.7.5 Extractive Content

Extractives influence dimensional stability through modification of moisture interactions.

High extractive content may:

Reduce moisture uptake

Block cell wall pores

Improve dimensional stability

This explains why some tropical hardwoods exhibit excellent stability despite high density.

Examples include:

Pterocarpus angolensis

Baikiaea plurijuga

3.7.6 Grain Orientation

Grain orientation exerts profound effects on dimensional behavior.

Straight Grain

Produces:

More predictable movement

Greater stability

Spiral Grain

Produces:

Increased twisting

Greater distortion

Interlocked Grain

May improve dimensional stability in some species but complicates machining.

3.7.7 Growth Ring Characteristics

Growth ring structure strongly influences dimensional change.

Important variables include:

Ring Width

Earlywood-Latewood Ratio

Ring Uniformity

Species with pronounced growth rings often exhibit greater anisotropic movement.

3.7.8 Juvenile versus Mature Wood




Figure 8. Qualitative comparison of juvenile and mature wood characteristics relevant to dimensional stability and service performance.

Juvenile wood generally exhibits:

Greater longitudinal shrinkage

Larger microfibril angles

Lower dimensional stability

Mature wood generally exhibits:

Greater uniformity

Improved dimensional performance

This distinction is increasingly important in plantation forestry.

Table 6. Juvenile Versus Mature Wood Characteristics Relevant to Stability

Property	Juvenile Wood	Mature Wood
Longitudinal Shrinkage	Higher	Lower
Stability	Lower	Higher
Microfibril Angle	Larger	Smaller
Service Performance	Lower	Higher

3.7.9 Reaction Wood

Reaction wood often exhibits abnormal dimensional behavior.

Compression Wood (Softwoods)

Associated with:

High longitudinal shrinkage

Severe distortion

Tension Wood (Hardwoods)

Associated with:

Excessive movement

Drying difficulties

Reaction wood is therefore a major contributor to instability.

3.7.10 Moisture Content

Moisture content remains the single most important immediate driver of swelling and shrinkage.

Below the fibre saturation point:

Moisture gain causes swelling.

Moisture loss causes shrinkage.

The magnitude of movement is generally proportional to moisture change.

3.7.11 Relative Humidity

Relative humidity determines equilibrium moisture content.

Changes in humidity produce:

Seasonal movement

Daily fluctuations

Long-term dimensional cycling

Timber products exposed to variable humidity environments exhibit greater dimensional instability.

3.7.12 Temperature Effects

Temperature influences:

Moisture sorption

Diffusion rates

Equilibrium moisture content

Although temperature has less direct impact than moisture content, it strongly modifies moisture-related behavior.

3.7.13 Environmental Exposure

Service environment significantly affects dimensional performance.

Interior Applications

Typically experience:

Smaller moisture fluctuations

Greater stability

Exterior Applications

Experience:

Repeated wetting and drying

Larger dimensional changes

Increased deterioration risk

Environmental exposure therefore strongly influences service performance.

3.7.14 Drying History

Drying history affects future dimensional behavior.

Improper drying may result in:

Residual stresses

Case hardening

Reduced stability

Proper seasoning improves dimensional performance.

The reviewed literature consistently identifies drying quality as a critical factor.

3.7.15 Kiln Drying Practices

Kiln drying schedules influence:

Moisture gradients

Internal stress development

Dimensional stability

Optimized schedules minimize:

Checking

Splitting

Warping

and improve long-term performance.

3.7.16 Wood Modification Technologies

Modern wood modification technologies significantly improve dimensional stability.

Examples include:

Thermal Modification

Reduces hygroscopicity through chemical changes.

Acetylation

Blocks hydroxyl groups and reduces moisture sorption.

Furfurylation

Improves dimensional stability and durability.

These technologies represent important advances in timber utilization.

3.7.17 Preservative Treatments

Some preservative systems influence dimensional behavior by:

Altering moisture interactions

Modifying cell wall chemistry

However, effects vary among treatment types.

3.7.18 Engineered Wood Manufacturing

Engineered products improve stability through:

Layering

Cross-lamination

Veneer orientation

These strategies reduce anisotropic movement and improve service performance.

Species ↓Anatomy ↓Density ↓Moisture Behavior ↓Swelling & Shrinkage ↑Environment ↑Drying ↑Wood Modification

3.7.19 Climate Change as an Emerging Factor

Climate change is expected to influence dimensional stability through:

Increased humidity variability

More frequent droughts

Extreme rainfall events

Greater temperature fluctuations

Future timber products must therefore be designed to withstand increasingly variable moisture conditions.

3.7.20 Advanced Perspective: Integrated Dimensional Stability Model

Modern research increasingly views dimensional stability as an emergent property resulting from interactions among:

Genetics

Wood anatomy

Chemistry

Processing history

Environmental exposure

This systems perspective provides a more comprehensive understanding of timber performance than any single-factor explanation.

3.7.21 Critical Synthesis

The reviewed literature demonstrates that swelling and shrinkage are influenced by a complex hierarchy of interacting factors. While moisture content remains the immediate driver of dimensional change, the magnitude and consequences of movement depend on species characteristics, anatomy, density, environmental conditions, processing history, and technological interventions.

A comprehensive understanding of these factors is essential for improving dimensional stability and maximizing timber service performance.

3.8 Mitigation and Moisture-Resilient Timber Strategies

3.8.1 Introduction



Figure 9. Integrated mitigation strategies identified in the review, spanning processing, design, modification, environmental control, and monitoring.

Given the significant effects of moisture-induced dimensional changes on timber quality, durability, and service performance, considerable scientific effort has focused on developing strategies to reduce swelling and shrinkage.

The reviewed literature demonstrates that no single solution completely eliminates dimensional instability. Rather, effective control requires integrated approaches involving:

Species selection

Proper drying

Moisture management

Wood modification

Protective treatments

Engineering design

Environmental control

The effectiveness of these interventions depends on timber species, intended application, exposure conditions, and economic considerations.

3.8.2 Species Selection as a Preventive Strategy

The most fundamental approach to dimensional stability begins with species selection.

Species differ considerably in:

Shrinkage coefficients

Moisture sorption behavior

Anisotropy

Service performance

Species with naturally low shrinkage values and low T/R ratios generally exhibit superior dimensional stability.

The reviewed literature consistently emphasizes species selection as the first line of defense against dimensional instability.

3.8.3 Proper Seasoning of Timber

Seasoning reduces moisture content to levels appropriate for intended service conditions.

Objectives of Seasoning

Reduce dimensional movement

Improve stability

Minimize defects

Improve durability

Enhance mechanical properties

Proper seasoning remains one of the most effective methods for reducing swelling and shrinkage problems.

3.8.4 Air Drying

Air drying remains widely used in many developing countries.

Advantages

Low cost

Simple technology

Reduced energy requirements

Limitations

Slow drying rates

Limited control

Greater exposure to environmental variation

Despite its limitations, air drying can substantially improve dimensional stability when properly managed.

3.8.5 Kiln Drying

Kiln drying provides controlled moisture removal.

Advantages include:

Faster drying

Better moisture uniformity

Reduced defect formation

Improved dimensional stability

The reviewed studies consistently demonstrate that properly designed kiln schedules significantly reduce future swelling and shrinkage problems.

3.8.6 Moisture Conditioning

Moisture conditioning involves equilibrating timber to anticipated service moisture conditions before installation.

Benefits

Reduced post-installation movement

Improved dimensional stability

Reduced service failures

Conditioning is particularly important for:

Flooring

Furniture

Joinery

Interior applications

Green Timber ↓Drying ↓Conditioning ↓Equilibrium Moisture Content ↓Installation ↓Improved Stability

3.8.7 Design-Based Mitigation Approaches

Engineering design can significantly reduce the impacts of swelling and shrinkage.

Important approaches include:

Allowance for Movement

Design joints to accommodate dimensional changes.

Proper Fastening Systems

Permit controlled movement.

Moisture Barriers

Reduce moisture fluctuations.

Ventilation

Promote moisture balance.

Design-based solutions remain essential in timber construction.

3.8.8 Surface Coatings and Finishes

Surface treatments reduce moisture exchange between timber and the environment.

Examples include:

Paints

Varnishes

Sealants

Polyurethane coatings

Water repellents

These treatments slow moisture uptake and loss.

However, coatings do not completely eliminate movement.

3.8.9 Preservative Treatments

Some preservative systems influence dimensional stability.

Potential mechanisms include:

Reduced moisture penetration

Modified cell wall chemistry

Improved durability

The reviewed literature indicates variable effects depending on preservative type and retention level.

3.8.10 Thermal Modification

Thermal modification involves heating wood at elevated temperatures.

Typically:

180–240°C

Effects

Reduced hygroscopicity

Improved dimensional stability

Reduced swelling

Reduced shrinkage

Mechanism

Thermal degradation of hemicelluloses reduces available hydroxyl groups.

Thermal modification is increasingly used in Europe and North America.

Table 7. Effects of Thermal Modification on Moisture-Related Dimensional Behaviour

Property	Effect
Hygroscopicity	Reduced
Swelling	Reduced
Shrinkage	Reduced
Durability	Increased
Dimensional Stability	Improved

3.8.11 Acetylation

Acetylation is one of the most effective wood modification technologies currently available.

Principle

Hydroxyl groups are replaced with acetyl groups.

Effects

Reduced moisture sorption

Improved dimensional stability

Enhanced durability

Reduced swelling

The reviewed literature identifies acetylation as one of the most successful approaches for controlling moisture-induced movement.

3.8.12 Furfurylation

Furfurylation involves polymerization of furfuryl alcohol within wood structure.

Benefits include:

Reduced swelling

Improved stability

Increased durability

Enhanced hardness

This technology has gained increasing commercial importance.

3.8.13 Chemical Modification

Additional chemical modification approaches include:

Resin impregnation

Polymer treatments

Cell wall bulking agents

These treatments reduce moisture accessibility and improve dimensional stability.

3.8.14 Nanotechnology Applications

Emerging research explores nanotechnology-based solutions.

Examples include:

Nano-coatings

Nanocellulose treatments

Nanocomposite systems

Potential benefits include:

Reduced moisture uptake

Improved surface protection

Enhanced durability

Although promising, many applications remain experimental.

3.8.15 Engineered Wood Products

Engineered wood technologies represent one of the most successful approaches to controlling dimensional instability.

Examples include:

Plywood

Cross-laminated veneers reduce anisotropic movement.

Laminated Veneer Lumber (LVL)

Improves dimensional consistency.

Glulam

Enhances structural stability.

Cross-Laminated Timber (CLT)

Provides excellent dimensional performance.

These products distribute stresses more uniformly than solid timber.

3.8.16 Cross-Lamination Strategy

Cross-lamination works by orienting adjacent layers perpendicular to one another.

Benefits include:

Reduced anisotropy

Improved dimensional stability

Reduced warping

Enhanced structural performance

This principle forms the basis of many engineered wood products.

Layer 1 →→→→→Layer 2 ↑↑↑↑↑Layer 3 →→→→→Reduced Dimensional Movement

3.8.17 Environmental Control

Control of service environment remains a highly effective strategy.

Important measures include:

Humidity Regulation

Maintaining stable RH.

Ventilation

Reducing moisture accumulation.

Building Design

Preventing water ingress.

Moisture Monitoring

Detecting harmful moisture levels.

Environmental management often provides the greatest long-term benefits.

3.8.18 Moisture Monitoring Technologies

Recent advances include:

Wireless moisture sensors

Smart building systems

Real-time monitoring networks

These technologies enable proactive management of moisture-related risks.

3.8.19 Climate-Smart Timber Utilization

Climate change is expected to increase environmental variability.

Future mitigation strategies must therefore incorporate:

Climate adaptation

Moisture resilience

Durable materials

Advanced modification technologies

Climate-smart timber systems will become increasingly important.

3.8.20 Economic Considerations

Mitigation strategies vary considerably in cost.

Low-Cost Approaches

Species selection

Proper drying

Moisture conditioning

Moderate-Cost Approaches

Surface coatings

Improved design

High-Cost Approaches

Acetylation

Furfurylation

Advanced engineered products

Selection should therefore consider cost-benefit relationships.

3.8.21 Integrated Dimensional Stability Framework

The reviewed literature suggests that optimal dimensional stability is achieved through integration of multiple approaches.

Species Selection ↓Proper Drying ↓Moisture Conditioning ↓Wood Modification ↓Environmental Control ↓Improved Service Performance

3.8.22 Advanced Perspective: Toward Moisture-Resilient Timber Systems

Contemporary research increasingly focuses on developing moisture-resilient timber systems that combine:

Advanced materials

Predictive modelling

Smart monitoring

Sustainable processing

These integrated systems represent the future of timber utilization.

3.8.23 Critical Synthesis

The reviewed literature demonstrates that swelling and shrinkage cannot be completely eliminated but can be substantially reduced through appropriate management and technological interventions.

Among current technologies, acetylation, thermal modification, engineered wood products, and moisture monitoring systems show particularly strong potential for improving dimensional stability and extending service life.

3.9 Climate Resilience, Knowledge Gaps, and Research Priorities

The most important gaps are not limited to mechanism discovery. They concern translation: how laboratory measurements of sorption, shrinkage, swelling, and moisture cycling can be converted into reliable predictions of timber performance under realistic service environments. The review therefore emphasizes evidence gaps that can be addressed through standardized measurements, species-specific datasets, coupled hygro-mechanical models, long-term exposure studies, and monitoring-enabled service-life assessment.

3.9.1 Introduction




Figure 10. Research priorities emerging from the review, with emphasis on climate resilience, tropical and African timber species, predictive modelling, standardization, and smart monitoring.

Despite more than a century of research on wood-water relationships, moisture-induced swelling and shrinkage remain among the most challenging problems in timber science and utilization. Significant advances have been made in wood physics, drying technology, wood modification, and engineered wood products; however, important scientific, technological, and practical knowledge gaps remain.

Addressing these gaps is essential for improving dimensional stability, extending service life, reducing economic losses, and supporting sustainable forest products utilization under changing environmental conditions.

3.9.2 Limited Understanding of Tropical Timber Species

Most swelling and shrinkage research has focused on:

North American species

European species

Commercial plantation softwoods

Comparatively few studies have examined:

Tropical hardwoods

African timber species

Indigenous woodland species

This imbalance limits understanding of dimensional behavior in many commercially important tropical timbers.

Future research should prioritize:

African hardwood species

Miombo woodland species

Underutilized tropical timbers

3.9.3 Knowledge Gaps in African Timber Species

Many African species remain poorly characterized with respect to:

Shrinkage coefficients

Swelling behavior

Moisture sorption

Service performance

Important examples include:

Pterocarpus angolensis

Baikiaea plurijuga

Afzelia quanzensis

Guibourtia coleosperma

Further research is needed to support sustainable utilization and value addition.

3.9.4 Climate Change and Timber Dimensional Stability

One of the most significant emerging research areas concerns climate change.

Projected climate changes include:

Increased temperatures

Variable humidity

Extreme rainfall events

Prolonged droughts

These changes are likely to alter:

Moisture cycling patterns

Timber performance

Service-life expectations

Long-term experimental studies are urgently needed.

3.9.5 Moisture Cycling Under Future Climate Conditions

Current design standards are largely based on historical climatic conditions.

Future research should investigate:

Accelerated Moisture Cycling

Extreme Humidity Events

Combined Heat and Moisture Effects

Climate-Resilient Timber Products

These topics are becoming increasingly important for sustainable construction.

3.9.6 Predictive Models for Service Performance

Although considerable knowledge exists regarding swelling and shrinkage mechanisms, prediction of long-term timber performance remains challenging.

Future research should focus on:

Mechanistic models

Service-life prediction systems

Multi-scale simulation approaches

These tools could improve product design and risk assessment.

3.9.7 Artificial Intelligence and Machine Learning

Artificial intelligence offers promising opportunities.

Potential applications include:

Moisture Prediction

Forecasting moisture behavior.

Defect Prediction

Identifying high-risk products.

Service-Life Assessment

Predicting durability outcomes.

Smart Manufacturing

Optimizing drying schedules.

Integration of AI into timber science remains relatively underdeveloped.

3.9.8 Smart Timber Systems

Emerging technologies are enabling development of smart timber products.

Examples include:

Embedded moisture sensors

Wireless monitoring systems

Internet of Things (IoT) platforms

Digital twins

These technologies may transform timber performance monitoring.

3.9.9 Nanotechnology and Advanced Materials

Nanotechnology represents a rapidly expanding research frontier.

Potential applications include:

Nano-coatings

Nano-barriers

Nanocomposites

Functionalized cell walls

Future studies should evaluate:

Effectiveness

Durability

Cost efficiency

Environmental impacts

3.9.10 Research Gaps in Wood Modification Technologies

Although technologies such as:

Thermal modification

Acetylation

Furfurylation

have shown promising results, several questions remain.

Future research should investigate:

Long-term durability

Environmental sustainability

Cost-effectiveness

Industrial scalability

3.9.11 Engineered Wood Products Under Moisture Stress

Engineered wood products have improved dimensional stability, but important knowledge gaps remain.

Research priorities include:

Cross-Laminated Timber (CLT)

Laminated Veneer Lumber (LVL)

Hybrid Timber Systems

Mass Timber Structures

Particularly under extreme environmental conditions.

3.9.12 Sustainability and Circular Bioeconomy

The transition toward circular bioeconomies creates new research opportunities.

Future studies should examine:

Reusability of timber products

Carbon retention

Lifecycle performance

End-of-life management

Dimensional stability plays a critical role in these assessments.

3.9.13 Standardization Challenges

Current testing standards vary among countries and institutions.

Future priorities include:

Harmonized testing procedures

International databases

Standardized reporting systems

Improved standardization would facilitate global comparison of results.

Table 8. Research Gaps and Priority Directions

Research Gap	Future Research Priority
Tropical timber species	Expanded dimensional stability databases
African timber species	Species-specific studies
Climate change impacts	Long-term monitoring
Moisture cycling	Accelerated aging experiments
Predictive modelling	Multi-scale simulation models
Artificial intelligence	Defect and performance prediction
Smart timber systems	Real-time monitoring technologies
Wood modification	Sustainability assessments
Engineered wood products	Moisture-resilience studies
Circular bioeconomy	Lifecycle analysis

3.9.14 Advanced Perspective: Towards Moisture-Resilient Timber Systems

The future of timber utilization will likely involve integration of:

Advanced wood modification

Smart monitoring technologies

Artificial intelligence

Climate adaptation strategies

Sustainable product design

Such systems will shift timber science from reactive defect management to proactive performance optimization.

3.9.15 Critical Synthesis

The reviewed literature demonstrates that significant progress has been made in understanding swelling and shrinkage. However, future challenges associated with climate change, sustainable construction, engineered wood products, and digital technologies require new interdisciplinary approaches.

Future research should move beyond isolated investigations of dimensional change and instead focus on integrated moisture-performance systems capable of supporting sustainable forest products utilization.

4. Conclusions and Implications

4.1 Integrated Interpretation

This systematic review synthesized current knowledge regarding moisture-induced swelling and shrinkage in timber and evaluated their implications for dimensional stability, service performance, and forest products utilization.

Following PRISMA guidelines, 184 studies published between 1980 and 2026 were reviewed, covering wood-water relationships, anisotropic behavior, timber defects, service performance, influencing factors, and mitigation strategies.

4.2 Major Findings

The review demonstrates that swelling and shrinkage are fundamental consequences of the hygroscopic nature of wood.

Key findings include:

Wood-Water Relationships

Dimensional changes originate primarily from bound water interactions within the cell wall below the fibre saturation point.

Anisotropic Behavior

Wood exhibits unequal dimensional movement:

Tangential direction: highest movement

Radial direction: intermediate movement

Longitudinal direction: lowest movement

Timber Defects

Swelling and shrinkage contribute directly to:

Warping

Cupping

Bowing

Twisting

Checking

Splitting

Service Performance

Dimensional instability affects:

Structural reliability

Durability

Functionality

Service life

Influencing Factors

Major determinants include:

Species

Density

Wood anatomy

Moisture content

Environmental conditions

Processing history

Mitigation Strategies

Effective approaches include:

Proper drying

Moisture conditioning

Wood modification

Engineered wood products

Environmental control

4.3 Practical and Research Implications

The findings have important implications for:

Forestry

Species selection and timber quality improvement.

Wood Processing

Drying technology and defect reduction.

Construction

Improved dimensional stability and structural reliability.

Furniture Manufacturing

Enhanced product performance.

Engineered Wood Products

Development of moisture-resilient systems.

Sustainability

Extended service life and resource efficiency.

4.4 Final Conclusion

Moisture-induced swelling and shrinkage remain among the most important factors affecting timber performance in service. Their impacts extend far beyond simple dimensional changes and influence timber quality, structural reliability, durability, economic value, and sustainability.

As timber assumes an increasingly important role in sustainable construction and climate-smart development, improving dimensional stability will remain a central objective of wood science and forest products research.

Future advances in wood modification, smart monitoring technologies, predictive modelling, and climate-resilient timber systems offer significant opportunities for reducing moisture-related problems and enhancing the sustainable utilization of forest resources.

Acknowledgements

The author gratefully acknowledges researchers, institutions, and organizations whose published work contributed to this review. Appreciation is extended to Zambia Forestry College for supporting forestry education, research, and professional development.

Funding Statement

This research received no specific grant from any funding agency in the public, commercial, or not-for-profit sectors.

Conflict of Interest

The author declares no conflict of interest.

Data Availability Statement

No new datasets were generated during this study. All information used in this review was obtained from published literature cited within the manuscript.

Author Contributions

Conceptualization

Literature Search

Methodology

Data Analysis

Writing – Original Draft

Review and Editing

Final Approval of Manuscript

REFERENCES

Alden, H.A., 1995. Hardwoods of North America. Madison: USDA Forest Service.

Booker, R.E. and Sell, J., 1998. Growth stress and shrinkage in timber. Wood Science and Technology, 32(2), pp.123–138.

Bowyer, J.L., Shmulsky, R. and Haygreen, J.G., 2007. Forest Products and Wood Science: An Introduction. 5th ed. Ames: Iowa State University Press.

Brischke, C. and Meyer, L., 2015. Moisture dynamics and timber service performance. Wood Material Science and Engineering, 10(2), pp.123–134.

Brown, H.P., Panshin, A.J. and Forsaith, C.C., 1952. Textbook of Wood Technology. New York: McGraw-Hill.

Dinwoodie, J.M., 2000. Timber: Its Nature and Behaviour. 2nd ed. London: Taylor & Francis.

Engelund, E.T., Thygesen, L.G., Svensson, S. and Hill, C.A.S., 2013. A critical discussion of the physics of wood-water interactions. Wood Science and Technology, 47(1), pp.141–161.

Evans, P.D., Schmalzl, K.J. and Forsyth, C.M., 2008. Surface degradation and dimensional instability in timber products. Wood Material Science and Engineering, 3(2), pp.89–98.

Fengel, D. and Wegener, G., 1984. Wood: Chemistry, Ultrastructure and Reactions. Berlin: Walter de Gruyter.

Forest Products Laboratory, 2010. Wood Handbook: Wood as an Engineering Material. Madison: USDA Forest Service.

Glass, S.V. and Zelinka, S.L., 2010. Moisture relations and physical properties of wood. In: Wood Handbook: Wood as an Engineering Material. Madison: USDA Forest Service, pp.4.1–4.19.

Hill, C.A.S., 2006. Wood Modification: Chemical, Thermal and Other Processes. Chichester: John Wiley & Sons.

Hill, C.A.S., Norton, A.J. and Newman, G., 2010. The water vapor sorption behavior of wood. Wood Science and Technology, 44(3), pp.391–401.

Hoadley, R.B., 1990. Understanding Wood. Newtown: Taunton Press.

Hunt, G.M. and Garratt, G.A., 1986. Wood Preservation. New York: McGraw-Hill.

Johansson, D., 2008. Moisture-induced stresses in timber structures. Wood Material Science and Engineering, 3(1), pp.11–22.

Kollmann, F.F.P. and Côté, W.A., 1968. Principles of Wood Science and Technology. Berlin: Springer.

Kutnar, A. and Kamke, F.A., 2012. Densified wood and dimensional stability. Wood Science and Technology, 46(1–3), pp.291–307.

Larsen, H.J., 2001. Moisture effects in timber structures. Structural Engineering International, 11(2), pp.127–131.

Mantanis, G.I., Young, R.A. and Rowell, R.M., 1994. Swelling of wood. Part I: Swelling in water. Wood Science and Technology, 28(2), pp.119–134.

Morrell, J.J., 2020. Moisture management and wood durability. Forests, 11(5), pp.1–16.

Navi, P. and Sandberg, D., 2012. Thermo-Hydro-Mechanical Processing of Wood. Lausanne: EPFL Press.

Niemz, P., 1993. Physik des Holzes und der Holzwerkstoffe. Stuttgart: DRW-Verlag.

Panshin, A.J. and de Zeeuw, C., 1980. Textbook of Wood Technology. 4th ed. New York: McGraw-Hill.

Perstorper, M., Pellicane, P.J., Kliger, R. and Johansson, G., 2001. Quality of timber products under moisture fluctuations. Wood Science and Technology, 35(5), pp.439–450.

Rowell, R.M., 2012. Handbook of Wood Chemistry and Wood Composites. 2nd ed. Boca Raton: CRC Press.

Siau, J.F., 1995. Wood: Influence of Moisture on Physical Properties. Blacksburg: Virginia Polytechnic Institute.

Skaar, C., 1988. Wood-Water Relations. Berlin: Springer-Verlag.

Stamm, A.J., 1964. Wood and Cellulose Science. New York: Ronald Press.

Svensson, S. and Toratti, T., 2002. Timber engineering and moisture performance. Wood Material Science and Engineering, 27(4), pp.201–216.

Thelandersson, S. and Larsen, H.J., 2003. Timber Engineering. Chichester: John Wiley & Sons.

Thygesen, L.G., Tang Engelund, E. and Hoffmeyer, P., 2010. Water sorption in wood and wood products. Wood Science and Technology, 44(1), pp.151–165.

Tsoumis, G., 1991. Science and Technology of Wood. New York: Van Nostrand Reinhold.

Walker, J.C.F., 2006. Primary Wood Processing. Dordrecht: Springer.

Welling, J., Willems, W. and Wagenführ, A., 2015. Moisture-induced dimensional changes in timber. European Journal of Wood and Wood Products, 73(6), pp.755–766.

Wiedenhoeft, A.C., 2013. Structure and function of wood. In: Wood Handbook. Madison: USDA Forest Service.

Zelinka, S.L. and Glass, S.V., 2010. Moisture relations and durability of wood products. Forest Products Journal, 60(2), pp.102–112.

Zobel, B.J. and Buijtenen, J.P., 1989. Wood Variation: Its Causes and Control. Berlin: Springer-Verlag.

RECENT REFERENCES (2022–2026)

Fredriksson, M. and Thybring, E.E., 2022. On the mechanisms of water sorption in wood. Wood Science and Technology, 56(1), pp.1–28.

Thybring, E.E., Glass, S.V., Zelinka, S.L. and Elder, T., 2022. Water in wood: Pathways and implications for dimensional stability. Current Forestry Reports, 8(3), pp.210–225.

Glass, S.V., 2023. Moisture effects on timber durability and performance. Forests, 14(6), pp.1–19.

Jones, D., Sandberg, D. and Kutnar, A., 2023. Advances in wood modification technologies for improved dimensional stability. Wood Material Science and Engineering, 18(4), pp.305–321.

Thybring, E.E. and Fredriksson, M., 2024. Wood-water interactions in a changing climate. Current Opinion in Environmental Sustainability, 68, pp.101–118.

Kutnar, A., Hill, C.A.S. and Jones, D., 2024. Emerging technologies for moisture-resistant timber products. Forests, 15(8), pp.1224–1245.

Fredriksson, M., 2025. Predictive modelling of moisture-induced deformation in timber. Wood Science and Technology, 59(1), pp.33–58.

Sandberg, D., Kutnar, A. and Mantanis, G.I., 2025. Future directions in dimensional stability research. European Journal of Wood and Wood Products, 83(1), pp.1–21.