

checkCIF/PLATON report

Structure factors have been supplied for datablock(s) muf-91-9h-64pc

THIS REPORT IS FOR GUIDANCE ONLY. IF USED AS PART OF A REVIEW PROCEDURE FOR PUBLICATION, IT SHOULD NOT REPLACE THE EXPERTISE OF AN EXPERIENCED CRYSTALLOGRAPHIC REFEREE.

No syntax errors found. CIF dictionary Interpreting this report

Datablock: muf-91-9h-64pc

| | | |
|------------------------|------------------------------------|---|
| Bond precision: | = 0.0000 A | Wavelength=0.71075 |
| Cell: | a=17.1300 (12) | b=17.1300 (12) c=17.1300 (12) |
| | alpha=90 | beta=90 gamma=90 |
| Temperature: | 100 K | |
| | Calculated | Reported |
| Volume | 5026.6 (11) | 5026.6 (11) |
| Space group | P -4 3 m | P -4 3 m |
| Hall group | P -4 2 3 | P -4 2 3 |
| Moiety formula | 2 (C9.24 H5.28 N0.50 O1.78 Zn0.55) | C84 H48 N6 O13 Zn4, C26.848 H15.342 O8.31 Zn2.557 |
| Sum formula | C18.48 H10.56 N 03.55 Zn1.09 | C110.85 H63.34 N6 O21.31 Zn6.56 |
| Mr | 375.04 | 2249.00 |
| Dx, g cm ⁻³ | 0.743 | 0.743 |
| Z | 6 | 1 |
| Mu (mm ⁻¹) | 0.808 | 0.807 |
| F000 | 1138.3 | 1138.0 |
| F000' | 1140.56 | |
| h, k, lmax | 19, 19, 19 | 19, 19, 19 |
| Nref | 1407 [782] | 1409 |
| Tmin, Tmax | | 0.652, 0.746 |
| Tmin' | | |

Correction method= # Reported T Limits: Tmin=0.652 Tmax=0.746

AbsCorr = MULTI-SCAN

Data completeness= 1.80/1.00

Theta (max)= 23.248

R(reflections)= 0.1305(965)

wR2(reflections)=
0.3557(1409)

S = 1.421

Npar= 33

The following ALERTS were generated. Each ALERT has the format

test-name_ALERT_alert-type_alert-level.

Click on the hyperlinks for more details of the test.

Alert level A

PLAT601_ALERT_2_A Unit Cell Contains Solvent Accessible VOIDS of . 1625 Ang**3

Alert level B

THETM01_ALERT_3_B The value of sine(theta_max)/wavelength is less than 0.575

Calculated sin(theta_max)/wavelength = 0.5553

PLAT049_ALERT_1_B Calculated Density Less Than 1.0 gcm-3 0.7434 Check

PLAT084_ALERT_3_B High wR2 Value (i.e. > 0.25) 0.36 Report

PLAT987_ALERT_1_B The Flack x is >> 0 - Do a BASF/TWIN Refinement Please Check

Alert level C

STRVA01_ALERT_4_C Flack test results are ambiguous.

From the CIF: _refine_ls_abs_structure_Flack 0.340

From the CIF: _refine_ls_abs_structure_Flack_su 0.020

PLAT041_ALERT_1_C Calc. and Reported SumFormula Strings Differ Please Check

PLAT053_ALERT_1_C Minimum Crystal Dimension Missing (or Error) ... Please Check

PLAT054_ALERT_1_C Medium Crystal Dimension Missing (or Error) ... Please Check

PLAT055_ALERT_1_C Maximum Crystal Dimension Missing (or Error) ... Please Check

PLAT077_ALERT_4_C Unitcell Contains Non-integer Number of Atoms .. Please Check

PLAT082_ALERT_2_C High R1 Value 0.13 Report

PLAT094_ALERT_2_C Ratio of Maximum / Minimum Residual Density 2.49 Report

PLAT250_ALERT_2_C Large U3/U1 Ratio for Average U(i,j) Tensor 2.8 Note

PLAT260_ALERT_2_C Large Average Ueq of Residue Including Zn1 0.187 Check

PLAT905_ALERT_3_C Negative K value in the Analysis of Variance ... -1.228 Report

PLAT911_ALERT_3_C Missing FCF Refl Between Thmin & STh/L= 0.555 2 Report

PLAT918_ALERT_3_C Reflection(s) with I(obs) much Smaller I(calc) . 3 Check

PLAT939_ALERT_3_C Large Value of Not (SHELXL) Weight Optimized S . 27.57 Check

Alert level G

FORMU01_ALERT_2_G There is a discrepancy between the atom counts in the

_chemical_formula_sum and the formula from the _atom_site* data.

Atom count from _chemical_formula_sum: C110.85 H63.34 N6 O21.31 Zn6.56

Atom count from the _atom_site data: C81.06 H55.68 N6 O9.908299 Zn1.0

ABSMU01_ALERT_1_G Calculation of _exptl_absorpt_correction_mu

not performed for this radiation type.

CELLZ01_ALERT_1_G Difference between formula and atom_site contents detected.

CELLZ01_ALERT_1_G ALERT: Large difference may be due to a

symmetry error - see SYMMG tests

From the CIF: _cell_formula_units_Z 1

From the CIF: _chemical_formula_sum C110.85 H63.34 N6 O21.31 Zn6.56

TEST: Compare cell contents of formula and atom_site data

| atom | Z*formula | cif sites | diff | |
|------|-----------|-----------|-------|--|
| C | 110.85 | 81.06 | 29.79 | |
| H | 63.34 | 55.68 | 7.66 | |
| N | 6.00 | 6.00 | 0.00 | |
| O | 21.31 | 9.91 | 11.40 | |
| Zn | 6.56 | 1.09 | 5.47 | |

| | | | |
|-------------------|--|--------|--------|
| PLAT002_ALERT_2_G | Number of Distance or Angle Restraints on AtSite | 10 | Note |
| PLAT003_ALERT_2_G | Number of Uiso or Uij Restrained non-H Atoms ... | 18 | Report |
| PLAT042_ALERT_1_G | Calc. and Reported Moiety Formula Strings Differ | Please | Check |
| PLAT045_ALERT_1_G | Calculated and Reported Z Differ by a Factor ... | 6.0000 | Check |
| PLAT068_ALERT_1_G | Reported F000 Differs from Calcd (or Missing)... | Please | Check |
| PLAT072_ALERT_2_G | SHELXL First Parameter in WGHT Unusually Large | 0.20 | Report |
| PLAT171_ALERT_4_G | The CIF-Embedded .res File Contains EADP Records | 3 | Report |
| PLAT172_ALERT_4_G | The CIF-Embedded .res File Contains DFIX Records | 11 | Report |
| PLAT174_ALERT_4_G | The CIF-Embedded .res File Contains FLAT Records | 3 | Report |
| PLAT178_ALERT_4_G | The CIF-Embedded .res File Contains SIMU Records | 2 | Report |
| PLAT180_ALERT_4_G | Check Cell Rounding: # of Values Ending with 0 = | 3 | Note |
| PLAT186_ALERT_4_G | The CIF-Embedded .res File Contains ISOR Records | 1 | Report |
| PLAT300_ALERT_4_G | Atom Site Occupancy of Zn0A Constrained at | 0.1667 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of O2 Constrained at | 0.5 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of O1 Constrained at | 0.0417 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of C12 Constrained at | 0.5 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of C13 Constrained at | 0.5 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of N1 Constrained at | 0.25 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of C10 Constrained at | 0.25 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of C11 Constrained at | 0.25 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of C14 Constrained at | 0.25 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of C15 Constrained at | 0.25 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of C16 Constrained at | 0.25 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of C17 Constrained at | 0.25 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of C18 Constrained at | 0.25 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of C19 Constrained at | 0.25 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of C20 Constrained at | 0.25 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of C21 Constrained at | 0.25 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of H12 Constrained at | 0.5 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of H13 Constrained at | 0.25 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of H17 Constrained at | 0.25 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of H18 Constrained at | 0.25 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of H19 Constrained at | 0.25 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of H20 Constrained at | 0.25 | Check |
| PLAT300_ALERT_4_G | Atom Site Occupancy of H21 Constrained at | 0.25 | Check |
| PLAT301_ALERT_3_G | Main Residue Disorder(Resd 1) | 100% | Note |
| PLAT304_ALERT_4_G | Non-Integer Number of Atoms in (Resd 1) | 17.34 | Check |
| PLAT315_ALERT_2_G | Singly Bonded Carbon Detected (H-atoms Missing). | C14 | Check |
| PLAT315_ALERT_2_G | Singly Bonded Carbon Detected (H-atoms Missing). | C34 | Check |
| PLAT432_ALERT_2_G | Short Inter X...Y Contact C13 ..C15 . | 2.75 | Ang. |
| | z,y,x = | 24_555 | Check |
| PLAT432_ALERT_2_G | Short Inter X...Y Contact N1 ..C15 . | 2.40 | Ang. |
| | z,y,x = | 24_555 | Check |
| PLAT432_ALERT_2_G | Short Inter X...Y Contact C14 ..C15 . | 3.18 | Ang. |
| | 1-x,y,1-z = | 9_656 | Check |
| PLAT432_ALERT_2_G | Short Inter X...Y Contact C14 ..C15 . | 3.18 | Ang. |
| | z,y,x = | 24_555 | Check |
| PLAT432_ALERT_2_G | Short Inter X...Y Contact C14 ..C15 . | 3.18 | Ang. |
| | 1-z,y,1-x = | 23_656 | Check |
| PLAT720_ALERT_4_G | Number of Unusual/Non-Standard Labels | 1 | Note |
| PLAT789_ALERT_4_G | Atoms with Negative _atom_site_disorder_group # | 32 | Check |

| | | | |
|-------------------|---|----|-------------|
| PLAT860_ALERT_3_G | Number of Least-Squares Restraints | 75 | Note |
| PLAT883_ALERT_1_G | No Info/Value for _atom_sites_solution_primary . | | Please Do ! |
| PLAT910_ALERT_3_G | Missing # of FCF Reflection(s) Below Theta (Min). | 4 | Note |
| PLAT913_ALERT_3_G | Missing # of Very Strong Reflections in FCF | 2 | Note |
| PLAT933_ALERT_2_G | Number of HKL-OMIT Records in Embedded .res File | 2 | Note |

| | | |
|----|----------------------|--|
| 1 | ALERT level A | = Most likely a serious problem - resolve or explain |
| 4 | ALERT level B | = A potentially serious problem, consider carefully |
| 14 | ALERT level C | = Check. Ensure it is not caused by an omission or oversight |
| 55 | ALERT level G | = General information/check it is not something unexpected |
| 13 | ALERT type 1 | CIF construction/syntax error, inconsistent or missing data |
| 17 | ALERT type 2 | Indicator that the structure model may be wrong or deficient |
| 10 | ALERT type 3 | Indicator that the structure quality may be low |
| 34 | ALERT type 4 | Improvement, methodology, query or suggestion |
| 0 | ALERT type 5 | Informative message, check |

It is advisable to attempt to resolve as many as possible of the alerts in all categories. Often the minor alerts point to easily fixed oversights, errors and omissions in your CIF or refinement strategy, so attention to these fine details can be worthwhile. In order to resolve some of the more serious problems it may be necessary to carry out additional measurements or structure refinements. However, the purpose of your study may justify the reported deviations and the more serious of these should normally be commented upon in the discussion or experimental section of a paper or in the "special_details" fields of the CIF. checkCIF was carefully designed to identify outliers and unusual parameters, but every test has its limitations and alerts that are not important in a particular case may appear. Conversely, the absence of alerts does not guarantee there are no aspects of the results needing attention. It is up to the individual to critically assess their own results and, if necessary, seek expert advice.

Publication of your CIF in IUCr journals

A basic structural check has been run on your CIF. These basic checks will be run on all CIFs submitted for publication in IUCr journals (*Acta Crystallographica*, *Journal of Applied Crystallography*, *Journal of Synchrotron Radiation*); however, if you intend to submit to *Acta Crystallographica Section C* or *E* or *IUCrData*, you should make sure that full publication checks are run on the final version of your CIF prior to submission.

Publication of your CIF in other journals

Please refer to the *Notes for Authors* of the relevant journal for any special instructions relating to CIF submission.

Validation response form

Please find below a validation response form (VRF) that can be filled in and pasted into your CIF.

start Validation Reply Form

_vrf_PLAT601_muf-91-9h-64pc

;

PROBLEM: Unit Cell Contains Solvent Accessible VOIDS of .

1625 Ang**3

RESPONSE: ...

;

end Validation Reply Form

PLATON version of 20/01/2022; check.def file version of 19/01/2022

Datablock muf-91-9h-64pc - ellipsoid plot

