

Warm to hot curing epoxy system based on Araldite® LY 564* / Aradur® 22962*

Araldite LY 564 is a low viscosity epoxy resin
Aradur 22962 is a cycloaliphatic polyamine

Applications	- Industrial composites - Structural composites		
Properties	Amine-cured laminating system showing excellent flexibility and high reactivity.		
Processing	- Wet lay-up - Filament Winding - Pressure Moulding - Resin Transfer Moulding (RTM) - Pultrusion		
Key data	Araldite LY 564		
	Aspect (visual)	clear liquid	
	Colour (Gardner, ISO 4630)	1 -2	
	Viscosity at 25 °C (ISO 12058-1)	1200 - 1400	[mPa s]
	Density at 25 °C (ISO 1675)	1.10 - 1.20	[g/cm ³]
	Flash point (ISO 2719)	185	[°C]
	Storage temperature (see expiry date on original container)	2 - 40	[°C]
	Aradur 22962		
	Aspect (visual)	clear liquid	
	Viscosity at 25 °C (ISO 12058-1)	5 - 20	[mPa s]
	Density at 25 °C (ISO 1675)	0.89 - 0.90	[g/cm ³]
	Flash point (ISO 2719)	≥ 110	[°C]
	Storage temperature (see expiry date on original container)	2 - 40	[°C]
Storage	Provided that Araldite LY 564 and Aradur 22962 are stored in a dry place in their original, properly closed containers at the above mentioned storage temperatures they will have the shelf lives indicated on the labels. Partly emptied containers should be closed immediately after use.		

* In addition to the brand name product denomination may show different appendices , which allows us to differentiate between our production sites:
e.g , BD = Germany, US = United States, IN = India, CI = China, etc.. These appendices are in use on packaging, transport and invoicing documents.
Generally the same specifications apply for all versions. Please address any additional need for clarification to the appropriate Huntsman contact

Processing data

Mix ratio	<i>Components</i>	<i>Parts by weight</i>	<i>Parts by volume</i>
	Araldite LY 564	100	100
	Aradur 22962	25	32
	We recommend that the components are weighed with an accurate balance to prevent mixing inaccuracies which can affect the properties of the matrix system. The components should be mixed thoroughly to ensure homogeneity. It is important that the side and the bottom of the vessel are incorporated into the mixing process. When processing large quantities of mixture the pot life will decrease due to exothermic reaction. It is advisable to divide large mixes into several smaller containers.		
Initial mix viscosity		[°C]	[mPa s]
(Hoeppler, ISO 12058-1B)		at 25	400-600
		at 40	100-200
Pot life		[°C]	[min]
(Tecam, 100 ml, 65 % RH)		at 23	110 - 150
Gel time		[°C]	[min]
(Hot plate)		at 80	20 30
		at 100	8 - 12
		at 120	3 - 6
		at 140	1.5 – 2.5
		at 160	0.5 – 1.5
The values shown are for small amounts of pure resin/hardener mix. In composite structures the gel time can differ significantly from the given values depending on the fibre content and the laminate thickness.			
Typical cure cycles	1 h 80 °C + 2 h 150 °C or 15 min 120°C + 2 h 150 °C The optimum cure cycle has to be determined case by case depending on the processing and the economic requirements.		

Properties of the cured, neat formulation

Glass transition temperature (IEC 1006, DSC, 10 K/min)	<i>Cure:</i>		<i>T_g [°C]</i>
	30 min 120 °C		108 - 115
	4 h 80 °C		100 - 110
	4 h 120 °C		120 - 128
	2 h 140 °C		125 - 135
	1 h 80 °C + 2 h 150 °C		128 - 138
Tensile test (ISO 527)	<i>Cure:</i>		<i>15 min 120 °C + 2 h 150 °C</i>
	Tensile strength	[MPa]	75 – 80
	Ultimate elongation	[%]	3.5 – 8.0
	Tensile modulus	[MPa]	2800 – 3300
Flexural test (ISO 178)	<i>Cure:</i>		<i>15 min 120 °C + 2 h 150 °C</i>
	Flexural strength	[MPa]	124 - 132
	Ultimate strength	[MPa]	120 - 135
	Ultimate elongation	[%]	9 - 11
	Flexural modulus	[MPa]	2700 - 2900
Fracture properties Bend notch test (PM 258-0/90)	<i>Cure:</i>		<i>15 min 120 °C + 2 h 150 °C</i>
	Fracture toughness K _{1C}	[MPa√m]	0.80 - 0.95
	Fracture energy G _{1C}	[J/m ²]	200 - 260
Water absorption (ISO 62)	<i>Immersion:</i>		<i>Cure:</i>
			<i>15 min 120 °C + 2 h 150 °C</i>
	4 days H ₂ O 23 °C	[%]	0.27 – 0.31
	10 days H ₂ O 23 °C	[%]	0.46 – 0.53

Properties of the cured, reinforced formulation

Interlaminar shear strength (ASTM D 2344)	Samples: 12 layers E-glass fabrics UD (425 g/m ²)		
	Laminate thickness = 3.1 - 3.25 mm		
	Fibre volume content: 59 - 63 %		
	Cure: 15 min 120 °C + 2 h 150 °C		
	Shear strength	[MPa]	60 -66

Handling precautions	Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information please consult the corresponding product safety data sheets and the brochure "Hygienic precautions for handling plastics products". Personal hygiene <i>Safety precautions at workplace</i> <table> <tr> <td>protective clothing</td><td>yes</td></tr> <tr> <td>gloves</td><td>essential</td></tr> <tr> <td>arm protectors</td><td>recommended when skin contact likely</td></tr> <tr> <td>goggles/safety glasses</td><td>yes</td></tr> </table> <i>Skin protection</i> <table> <tr> <td>before starting work</td><td>Apply barrier cream to exposed skin</td></tr> <tr> <td>after washing</td><td>Apply barrier or nourishing cream</td></tr> </table> <i>Cleansing of contaminated skin</i> Dab off with absorbent paper, wash with warm water and alkali-free soap, then dry with disposable towels. Do not use solvents <i>Disposal of spillage</i> Soak up with sawdust or cotton waste and deposit in plastic-lined bin <i>Ventilation</i> <table> <tr> <td>of workshop</td><td>Renew air 3 to 5 times an hour</td></tr> <tr> <td>of workplaces</td><td>Exhaust fans. Operatives should avoid inhaling vapours</td></tr> </table>	protective clothing	yes	gloves	essential	arm protectors	recommended when skin contact likely	goggles/safety glasses	yes	before starting work	Apply barrier cream to exposed skin	after washing	Apply barrier or nourishing cream	of workshop	Renew air 3 to 5 times an hour	of workplaces	Exhaust fans. Operatives should avoid inhaling vapours
protective clothing	yes																
gloves	essential																
arm protectors	recommended when skin contact likely																
goggles/safety glasses	yes																
before starting work	Apply barrier cream to exposed skin																
after washing	Apply barrier or nourishing cream																
of workshop	Renew air 3 to 5 times an hour																
of workplaces	Exhaust fans. Operatives should avoid inhaling vapours																
First aid	Contamination of the eyes by resin, hardener or mix should be treated immediately by flushing with clean, running water for 10 to 15 minutes. A doctor should then be consulted. Material smeared or splashed on the <i>skin</i> should be dabbed off, and the contaminated area then washed and treated with a cleansing cream (see above). A doctor should be consulted in the event of severe irritation or burns. Contaminated clothing should be changed immediately. Anyone taken ill after <i>inhaling</i> vapours should be moved out of doors immediately. In all cases of doubt call for medical assistance.																
Note	Araldite® and Aradur® are registered trademarks of Huntsman LLC or an affiliate thereof in one or more countries, but not all countries.																

Huntsman LLC ®Registered trademark	IMPORTANT: The following supersedes Buyer's documents. SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.
	