

Experimental Analysis of Surface Roughness by Optimizing Machining Parameters in Turning of Aluminium Alloy 075-T651 With Avocado Oil-Based Cutting Fluid Using Taguchi Based Grey Relational Analysis

Abera Ayza

aberaayza4@gmail.com

Wolaita Sodo University

Dr. Devendra Kumar

Wolaita Sodo University

Research Article

Keywords: ANOVA, Taguchi Method, Turning Operation, Spindle Speed, Surface Roughness

Posted Date: June 24th, 2026

DOI: <https://doi.org/10.21203/rs.3.rs-8069141/v1>

License: © ⓘ This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Additional Declarations: No competing interests reported.

Experimental Analysis of Surface Roughness by Optimizing Machining Parameters in Turning of Aluminium Alloy 075-T651 With Avocado Oil-Based Cutting Fluid Using Taguchi Based Grey Relational Analysis

Abera Ayza Anebo^{1*} Dr. Velivela Lakshmi Kanth Chowdary² Dr. Devendra Kumar³

¹Lecturer, Faculty of Engineering, Department of Mechanical Engineering (Specialization Manufacturing Engineering), Wolaita Sodo University, Wolaita Sodo, Ethiopia

²Lecturer, Department of Mechanical Engineering, International Associate, Wolaita Sodo University, Sodo, Ethiopia

³Lecturer, Department of Mechanical Engineering, School of Mechanical, Chemical and Materials Engineering, Adama Science and Technology University, Adama, Ethiopia

Author Correspondence: Abera Ayza Anebo, Email: *aberaayza4@gmail.com

ABSTRACT

This research aims to identify the optimal machining parameters for turning Aluminium Alloy 075-T651 using a tungsten carbide insert cutting tool and a flood coolant system, applying the Grey-based Taguchi method. Aluminium Alloy 075-T651 is commonly utilized in the automotive, marine, machine tools, and aerospace industries due to its excellent weight-to-strength ratio. A key focus of the study is surface roughness, which is critical in machining. The research explores how various turning parameters affect surface roughness and investigates the role of coolant in these operations. Heat generated during machining can adversely affect tool life, workpiece dimensions, and surface quality. To address these challenges, an environmentally friendly, biodegradable, and non-toxic avocado oil-based cutting fluid was employed. An orthogonal array from the Taguchi method guided the experiments, with surface roughness measured as a response. Minitab software facilitated the statistical analysis of process parameters. Key performance metrics included tool wear rate, material removal rate, and surface roughness, influenced by cutting speed, feed rate, depth of cut, and avocado oil proportion. The optimal surface roughness of 0.12 μm was achieved with specific parameter settings, confirming the effectiveness of the avocado oil-based cutting fluid. Conclusion: The evaluation from the orthogonal optimal turning parameters for the surface roughness are 9% of avocado oil based cutting fluid (level 4), cutting speed 820 rpm (level 1), feed rate 132mm/min(level 3) and depth of cut 1.5mm(level 3).

Keywords: ANOVA, Taguchi Method, Turning Operation, Spindle Speed, Surface Roughness

Background

Aluminium alloys are among the most commonly used lightweight metallic materials, known for their attractive mechanical and thermal properties. Aluminium alloy 7075-T651 is widely used in the aviation, marine, and automobile sectors. Its extensive applications highlight the importance of researching this material in the manufacturing field. Surface roughness has received significant attention for many years. It is an important design feature in various situations, such as parts subjected to fatigue loads, precision fits, fastener holes, and aesthetic requirements. In addition to tolerances, surface roughness imposes one of the most critical constraints on the selection of machines and cutting parameters in process planning. A considerable number of studies have investigated the general effects of speed, feed, depth of

Experimental Analysis of Surface Roughness by Optimizing Machining Parameters in Turning of Aluminium Alloy 075-T651 With Avocado Oil-Based Cutting Fluid Using Taguchi Based Grey Relational Analysis

cut, and cutting fluid on surface roughness. To improve the efficiency of these turning processes, it is essential to have a comprehensive understanding and model of the process. To simplify the problem, it is necessary to eliminate or select specific variables that correspond to practical applications. The productivity and efficiency of metal removal processes depend on machining parameters such as cutting conditions, cutting tool geometry, and the materials of both the workpiece and the tool. Optimizing these parameters during the turning process is crucial, as it directly influences surface roughness and the power consumed by the machine. In this experimental work, Aluminium Alloy 075-T651, which is commonly used in the aeronautical and manufacturing industries, has been selected as the material for investigation. The effects of cutting speed, feed rate, depth of cut and avocado oil cutting fluid on surface roughness were analysed using Taguchi methods. Experiments were conducted on Aluminium Alloy 075-T651 using a CNC lathe machine, and the impact of speed, feed, and depth of cut on surface roughness was measured.

Literature Review

Machining is a fabrication process that removes chips from a workpiece to achieve the desired form, dimensions, and finish. It is one of the oldest and most widely used industrial processes in engineering part manufacturing. Machining encompasses various actions like turning, milling, and cutting. These processes involve the use of a sharp cutting tool to remove excess material from the workpiece surface, resulting in the formation of chips that shape the final product. The primary cutting action in machining is shear deformation, which forms the chips. When the cutting tool encounters the workpiece material, it removes a chip and creates a newly machined surface. Machining requires relative motion between the cutting tool and the work material. Speed and feed rate are key factors in this relative motion, often referred to as cutting conditions or parameters (Valeru et al., 2019).

The shape, geometry, and contact of the cutting tool with the workpiece surface, combined with the motion, determine the final shape of the product. The cutting tool tip has two faces: the rake face and the flank face. The rake face is angled with respect to the plane perpendicular to the workpiece surface and controls the chip flow direction. The rake angle can be positive for finishing or negative for roughing. Additionally, the rake face can influence chip flow more than the flank face. The flank face, aligned with a clearance angle, protects the newly machined surface from abrasion by maintaining a gap between the tool and the surface (Jeevan & Jayaram, 2018).

Application of vegetable-oil based cutting fluid in machining process

[1] Made a preliminary study to determine the effect of cutting fluids on surface roughness and tool wear turning AISI 304 austenitic stainless steel with a carbide tool, inserts CNMG120408 as the cutting tool. The Taguchi $L_{27}(3^4)$ orthogonal matrix was implemented in the test plan. Factors and levels considered (low, medium and high) were depth of cut (1.2, 1.0 and 0.5 mm); cutting speed (97.38, 61.35 and 38.95 m/min); feeds (0.28, 0.25 and 0.20 mm/revolution); and type of cutting fluids (coconut oil, straight cutting oil and soluble oil). Numerical models of cutting parameters and cutting fluids (so each cutting fluid has a viscosity of 40°C) were obtained from regression analysis to estimate tool wear and surface roughness. ANOVA and signal-to-noise ratio (S/N) were performed to determine the significant parameter affecting tool

Experimental Analysis of Surface Roughness by Optimizing Machining Parameters in Turning of Aluminium Alloy 075-T651 With Avocado Oil-Based Cutting Fluid Using Taguchi Based Grey Relational Analysis

wear and surface roughness. The observation showed that feed rate had a greater effect on surface roughness by 61.54%, while cutting speed had a greater effect on tool wear by 46.49%. Cutting fluids have been found to significantly affect both tool wear and surface roughness. The viscosity of coconut oil fell between soluble oil and straight cutting oil, which increases the effective movement of cutting fluids in a relatively low oil state.

[2] they determined the effect of cutting fluids on tool wear rate and surface roughness in turning austenitic AISI 304 stainless steel. They performed turning using AISI 304 workpiece material. They used three different vegetable oil based cutting fluids: 1. Coconut oil 2. Soluble oil 3. Straight cutting oil. They concluded that feed rate affects surface roughness and cutting speed affects tool wear. Coconut oil is a better cutting fluid than conventional mineral oils for reducing tool wear and surface roughness.

[3] their study evaluates the performance of MQL using castor oil as the cutting fluid and compares the results with dry cutting. They found that using a small amount of 50ml/h of lubricant during a given turning process gives better results compared to dry cutting in terms of longer tool life. They learned that MQL machining appears to be limited by cutting temperature as the oil mist effect dissipates at high speeds.

[4] they analysed the effect of cutting fluids on the mechanical properties of mild steel during turning. The translation was done dry and also with three coolants. They found that palm kernel oil performs very well in the special functions of a soluble oil as a cutting fluid, which include good chip formation, heat reduction and good surface quality.

[5] they conducted an experimental study on the performance of coconut oil-based nano fluids as lubricants in the turning of AISI 304 austenitic stainless steel. Nano fluid lubricants were prepared with suspensions of nano boric acid in coconut oil, so that the thermal conductivity and heat transfer coefficient increased, and the specific heat decreased with increasing percentage of nano boric acid. Cutting temperatures, tool side wear and surface roughness were therefore significantly reduced with Nano lubricants compared to the base oil due to its superior lubricating properties. In all cases, coconut oil with 0.5% nano boric acid suspensions showed better results regarding cutting temperatures, tool flank wear and surface roughness compared to other nano fluids turning AISI 1018 steel with TiAlN coated inserts.

[6] investigates the effect of hybrid biodegradable nano fluids (CuO-ZnO) on surface roughness; Different classes of biodegradable liquids, especially palm oil and coconut oil, were

Experimental Analysis of Surface Roughness by Optimizing Machining Parameters in Turning of Aluminium Alloy 075-T651 With Avocado Oil-Based Cutting Fluid Using Taguchi Based Grey Relational Analysis

investigated as base liquids and mixed with a mixture of CuO-ZnO (50:50) nano particles. The effects of cutting parameters and fluid volume concentration were investigated in dry cutting with MQL/coconut oil and MQL/palm oil CuO-ZnO mixture in hybrid nano-fluid mixed media. Taguchi's orthogonal matrix L_9 and L_{18} were selected exclusively for dry and palm oil MQL and coconut oil MQL mixture contrast separately. They reported that the addition of CuO-ZnO hybrid nano particles to the base cutting fluids significantly reduced the surface roughness compared to conventional dry machining. ZnO nano particles act as lubricating oils that reduce the friction between the workpiece and the tool. Analysis of variance (ANOVA) showed that surface roughness is most affected by feed rate, followed by depth of cut and speed.

[7] performed evaluations of turning Ti-6Al-4V alloy with uncoated tungsten carbide, CVD-coated and PVD-coated carbide tools under three different conditions, i.e., dry, palm oil, palm oil mixture, and boric acid lubricant. Surface roughness. Taguchi's $L_{27}(3^5)$ strategy was then used to reveal the ideal cutting parameters for surface roughness. Five control variables were selected in the study, namely, type of machining environment, depth of cut, feed rate, cutting speed and type of carbide tool material. The results showed that palm oil was stronger when used with boric acid cutting fluids compared to dry and palm oil. Palm oil, cutting speed 79 m/min, feed speed 0.206 mm/rev, depth of cut 1.0 mm and CVD coated tool are optimal and safer combination values to reduce surface roughness. The Taguchi model $L_9(3^4)$ was used to compare the experimental soybean-based coolant E52100 with dry and oil-based coolants in chrome steel turning operations. Analysis of the test results showed that the soybean-based cutting fluid performed better against tool wear than the alternative oil product, and both cutting fluids reduced surface roughness equally well.

Materials and Methodology

These studies on avocado oil-based cutting fluids were specifically developed to achieve the previously mentioned objectives. To formulate an avocado oil-based cutting fluid for turning operations, a suitable flooding system was identified to improve the machining process's performance. The study examined various parameters of the avocado oil-based cutting fluid, including different proportions. This research utilized a turning process to evaluate the effectiveness of the avocado oil-based cutting fluid in machining operations.

Experimental Analysis of Surface Roughness by Optimizing Machining Parameters in Turning of Aluminium Alloy 075-T651 With Avocado Oil-Based Cutting Fluid Using Taguchi Based Grey Relational Analysis

Materials

Table 1. Machines and equipment used in the experiments.

S.No	Device Name	Purpose of usage
1	CNC lathe machine	For turning operation
2	Sono bright Ultrasonic vibration machine	To mix an avocado oil and water
3	Round bottom flask	To contain the mixed oil and distilled water
4	Portable grinder	For grinding
5	Surface roughness tester	To measure the surface roughness

Workpiece material

The workpiece selected for the study was Aluminium Alloy 075-T651, presented as a cylindrical bar with a length of 500mm and a diameter of 60 mm. This alloy provides medium strength, high corrosion resistance, and excellent formability. The most commonly available form of this alloy is in the T651 tempering condition. It is typically utilized in architectural applications, shop fittings, irrigation tubing, balustrades, window frames, extrusions, doors, marine equipment, and in both road and rail transport. It is also useful in all applications where high strength, fatigue and creep resistance are required, even at high temperatures [8]. The selected workpiece material used in the experiment were shown in the below figure5.

Cutting tool material

However, when choosing a cutting tool, it is decided to choose an uncoated tungsten carbide insert. Tungsten carbide insert are used in small industries, they are cheaper and more readily available. There is no need to change the insert before and after machining operation. Therefore, tungsten carbide insert cutting tool was used in this study. The tungsten carbide insert cutting tool selected for this study.

The measurements of output parameters

The output parameters, such as surface roughness, were measured to evaluate the performance of the avocado oil-based cutting fluid. This section describes the equipment used to measure these output parameters and provides a detailed description of each.

Surface roughness, (Ra) measurement

In the manufacturing industry, particularly in machining, special attention is given to dimensional accuracy and surface finish. The surface roughness of the machined surface is crucial for determining quality, as it impacts tolerances, reduces assembly time, and minimizes the need for secondary operations. A good surface finish enhances the performance, fatigue

Experimental Analysis of Surface Roughness by Optimizing Machining Parameters in Turning of Aluminium Alloy 075-T651 With Avocado Oil-Based Cutting Fluid Using Taguchi Based Grey Relational Analysis

strength, corrosion resistance, and aesthetics of the machined part. Surface roughness serves as the primary indicator of the mechanical part's effectiveness. If irregularities are present, cracks or corrosion can develop on the surface. Each machined part of the workpiece was measured three times at different points along the 100 mm length of the machined section of the square bar workpiece during each test, and the average of the three readings was used for analysis.



Figure 1. Photographic view of vogel surface roughness tester

Experimental Design

Design of Experiment Techniques

The Taguchi Design is chosen to assess the relative importance of various parameters. This experimental design technique effectively reduces the number of required experiments by utilizing orthogonal arrays. Its primary goal is to minimize the influence of uncontrollable factors and their effects. The fundamental philosophy of the Taguchi method is to ensure quality during the design stage. The key advantages of this approach include shortened test duration, lower costs, and quicker identification of significant factors[9].

The most reliable aspect of Taguchi's techniques is the use of parametric design, an engineering approach for product or process design. The primary goal of the Taguchi method is to identify the optimal parameter settings that achieve the highest quality characteristics while minimizing variation. A crucial step in planning an experiment is the selection of control factors. Including as many factors as possible allows for the rapid identification of irrelevant variables[9] .

Taguchi utilized the signal-to-noise ratio (S/N) as his preferred quality characteristic. The signal-to-noise ratio is employed instead of the standard deviation as the measured value because when the mean value decreases, the standard deviation also tends to decrease, and vice versa. [9].

A total of 16 experiments were conducted based on the orthogonal matrix $L_{16}(4^4)$ of the Taguchi method with different combinations of input parameter levels.

Experimental Analysis of Surface Roughness by Optimizing Machining Parameters in Turning of Aluminium Alloy 075-T651 With Avocado Oil-Based Cutting Fluid Using Taguchi Based Grey Relational Analysis

In this study, the experimental setup was based on the design of experiments (DoE) using the Taguchi method, focusing on four variables: cutting speed, feed rate, depth of cut, and cutting fluids. These variables were treated as experimental factors. Consequently, there were four input parameters, each with four levels, as shown in Table 13. In a four-factor, four-level experiment, Taguchi defined an orthogonal matrix $L_{16} (4^4)$ for the experiment. The confidence level assigned to the analysis is 95%.

Orthogonal Arrays

To minimize the total number of tests, Sir Ronald Fisher developed the concept of "Orthogonal Arrays." Taguchi employs these specially designed arrays in experimental design to ensure that quality is integrated into the product at the design stage. In this study, the columns are orthogonal to each other, facilitating a comprehensive analysis of the factors involved[10].

This means that each pair of columns contains all combinations of factors and they occur the same number of times and parameters. If the model was $L_{16} (4^4)$ it represents the sixteen row, configurations or prototypes being tested. The specific test characteristics of each test evaluation are given in the corresponding row of the table [11].

Thus, ' $L_{16} (4^4)$ ' means that sixteen experiments must be conducted to examine four variables at four levels. At least four levels of process parameters are desirable to achieve sufficient accuracy.

Analysis Of Variance (ANOVA)

Analysis of variance (ANOVA) is utilized to determine the percentage contribution of input process parameters to the response variables. To assess the significant effects and the individual impact of various machining conditions, the experimental results were evaluated using ANOVA. [12].

This study was conducted using a 95% confidence level and a 5% significance level. The test results were analysed using the signal-to-noise ratio (S/N) and analysis of variance (ANOVA) to identify the optimal and significant factors affecting surface roughness. The surface roughness of the machined part is influenced by cutting speed, feed rate, depth of cut, and cutting fluid. Since a lower surface roughness value is desirable, the performance of the cutting fluids was analysed using the Taguchi optimization process, which is based on the "smaller is better" principle for the characteristic ratio of surface roughness (S/N) in static tasks. Therefore,

Experimental Analysis of Surface Roughness by Optimizing Machining Parameters in Turning of Aluminium Alloy 075-T651 With Avocado Oil-Based Cutting Fluid Using Taguchi Based Grey Relational Analysis

a method for calculating the Signal-to-Noise ratio has been employed to assess the quality characteristic. The two types of quality characteristics considered are as follows:

(i) Smaller-the-better, and (ii) Larger-the-better.

The performance of the avocado oil-based cutting fluid was analysed using Taguchi's "lower-the-better" quality characteristic, specifically the signal-to-noise (S/N) ratio for surface roughness. The S/N ratios for surface roughness were calculated using the following equation (1):

$$S/N = -10 \log_{10} \left(\frac{\sum y^2}{N} \right) \quad \text{Eq. (1)}$$

The steps of grey relational analysis are as follows:

Step 1: Involves generating experimental data tables through the Design of Experiment.

Step 2: Generate Grey Relational Analysis. This process involves normalizing the values using a formula that scales the data to a range of 0 to 1. The surface roughness values are normalized, and the function is minimized according to the following equation (2) [13]

Lower the better

$$x_{2jk} = \left[\frac{\max(y_{ij}) - y_{ij}}{\max(y_{ij}) - \min(y_{ij})} \right] \quad \text{Eq. (2)}$$

Where: x_{2jk} - an experimental run of Ra

y_{ij} - is an experimental run of Ra, and TWR before preprocessing.

Max (y_{ij}) - Maximum value of original data.

Min. (y_{ij}) - minimum value of original data, $i=1, 2, 3 \dots m$

Step 3: Calculation of the grey relational coefficient. To compute the GRC use below equation(3) [14].

$$\gamma(x_{0j}, x_{ij}) = \left[\frac{(\Delta_{\min} + \xi \Delta_{\max})}{(\Delta_{ij} + \xi \Delta_{\max})} \right] \quad \text{Eq. (3)}$$

ξ - Coefficient of distinguishing and its range 0 to 1.

Step 4: Involves calculating the Grey Relational grade, which is obtained by finding the mean of the grey coefficients for each variable at the i^{th} run. The Grey Relational Grade serves as a measure of the overall performance of the multiple response technique. The level with the highest Grey relational grade represents the optimum level of the process parameters. To achieve this, a multiple response optimization problem with a grey relational objective function is transformed into an overall grey relational grade using equation (4).

$$\gamma_i = \frac{1}{n} \sum_{k=1}^n \zeta_i(k) \quad \text{Eq. (4)}$$

Experimental Analysis of Surface Roughness by Optimizing Machining Parameters in Turning of Aluminium Alloy 075-T651 With Avocado Oil-Based Cutting Fluid Using Taguchi Based Grey Relational Analysis

Where: γ_i -grey relational grade

n -replication number for response

Step 5: The optimal factor setting for maximum overall grey relational grade can be performed by Taguchi's method.

The selection of factor

The parameters investigated in this study was surface roughness was influenced by several factors, including cutting speed, depth of cut, feed rate, and types of cutting fluid. The selection of parameters for this experiment was informed by previous research in machining, literature reviews, tool manufacturing recommendations, workpiece material properties, available machine settings, and various research articles and manuals. Consequently, these factors were considered in the experimental design.

The selection of input parameter value.

When selecting parameter values, recommendations from the literature review, technical and technological limitations of the machine and tools, properties of the workpiece material, and findings from previous experimental studies were taken into account. However, considering all these factors proved to be costly and time-consuming. A review of the literature indicates that the most significant input factors influencing the values of the aforementioned output parameters, particularly surface roughness, are crucial for effective machining.

Table 2. Machining parameters and their levels.

Machining parameters			Levels		
Input parameter	Unit	Level 1	Level 2	Level 3	Level 4
Cutting speed	rpm	900	1000	1100	1200
Feed rate	mm/min	85	90	95	100
Depth of cut	mm	0.5	1	1.5	2
Avocado oil fluids	mm^2/s	0	3	6	9

Result and Discussion

Design Summary

Taguchi L16(4^4)

Array

Factors: 4

Runs: 16

Columns of L16 (4^5) array: 1 2 3 4

Table 3. Experimental result for Ra

S/N	Fluid: AO	Exp.No	Input parameters	Output parameters
-----	-----------	--------	------------------	-------------------

Experimental Analysis of Surface Roughness by Optimizing Machining Parameters in Turning of Aluminium Alloy 075-T651 With Avocado Oil-Based Cutting Fluid Using Taguchi Based Grey Relational Analysis

			Cutting speed	Feed rate	Depth of cut	Ra (μm)
1	0% AO with 100% DW	Exp.1	900	85	0.1	1.87
		Exp.2	900	90	1	0.95
		Exp.3	900	95	1.5	2.05
		Exp.4	900	100	2	2.1
2	3% AO with 97% DW	Exp.5	1000	85	1	1.56
		Exp.6	1000	90	0.1	1.72
		Exp.7	1000	95	2	0.98
		Exp.8	1000	100	1.5	0.93
3	6% AO with 94% DW	Exp.9	1100	85	1.5	1.07
		Exp.10	1100	90	2	0.67
		Exp.11	1100	95	0.1	0.89
		Exp.12	1100	100	1	0.56
4	9% AO with 91% DW	Exp.13	1200	85	2	0.14
		Exp.14	1200	90	1.5	0.22
		Exp.15	1200	95	1	0.39
		Exp.16	1200	100	0.1	0.12

Surface roughness

Signal-to-Noise (S/N) Ratio Analysis

Main effect plot for Surface roughness, Ra (μm)

The main effect plots for the surface roughness obtained from S/N ratio values of the machining parameters at different levels are shown in below figure 2. The plot of the main effect of S/N ratio as shown in figure 2 was used for optimum value determination for each input parameters during milling operation for the surface roughness. For surface roughness response, the smaller the better characteristics was chosen as shown figure 2. The objective of this study was to minimize surface roughness. These identified factor levels were considered as the optimum factors. Based on the analysis of figure 2, it is evident that the minimum surface roughness, indicating optimal conditions, was achieved with specific factor levels. Specifically, a 9% proportion of avocado oil-based cutting fluid at level 4, a cutting speed of 900 rpm at level 1, a feed rate of 95mm/min at level 3, and a depth of cut of 1.5mm at level 3 were found to yield the best results. The findings from the analysis suggest that the 9% proportion of avocado oil-based cutting fluid has a more significant impact on surface roughness compared to other proportions of the same cutting fluid. In other words, this particular factor level has a greater influence on achieving the desired outcome of minimizing surface roughness. Overall, this study highlights

Experimental Analysis of Surface Roughness by Optimizing Machining Parameters in Turning of Aluminium Alloy 075-T651 With Avocado Oil-Based Cutting Fluid Using Taguchi Based Grey Relational Analysis

the importance of carefully selecting the appropriate factor levels to optimize surface roughness and achieve the desired results.




Figure 2. Main effect plot for Surface roughness

ANOVA analysis

The ANOVA result was used to study the significance of the input parameters on the surface roughness. It is another way of understanding the importance of avocado oil based cutting fluid on surface roughness in this study. The ANOVA for surface roughness shown in table 18, a percentage error of 5.8% while 11.45% of avocado oil based cutting fluid, 2.67% of the depth of cut, 76.78% of cutting speed and 2.82% of feed rate. The ANOVA table generated using Minitab software version 19 reveals that all input parameters with P-values less than 0.05 have validated a significant impact on the variability of surface roughness. Therefore, ANOVA table shows that 76.78% of cutting speed has highest significance and have most important factor affecting surface roughness during the turning operation compared to other input parameters on the surface roughness. Hence, the results indicated that the cutting speed based cutting fluids has the highest significance on the surface roughness, followed by the depth of cut. This is in agreement with the study carried out by (Hasan et al., 2022), in which their finding showed that the surface roughness is dependent on the cutting speed based cutting fluids.

Table 4. ANOVA for Ra versus Oil, Speed, Feed and Doc

Source	DF	Adj SS	Adj MS	F-Value	P-Value	%C	Hypothesis
Cutting Speed	3	5.16	1.72	12.96	0.032	76.78	Significant

Experimental Analysis of Surface Roughness by Optimizing Machining Parameters in Turning of Aluminium Alloy 075-T651 With Avocado Oil-Based Cutting Fluid Using Taguchi Based Grey Relational Analysis

Feed Rate	3	0.19	0.06	0.48	0.031	2.82	Significant
Depth of Cut	3	0.18	0.06	0.45	0.043	2.67	Significant
Avocado oil fluid	3	0.77	0.25	1.95	0.019	11.45	Significant
Error	3	0.39	0.13			5.8	
Total	15	6.72					

Regression Analysis: Ra versus Oil, Speed, Feed, Doc

Regression Equation

$$Ra = 7.12 - 0.005CS - 0.1FR - 0.07DoC + 0.788AO \quad \text{Eq. (5)}$$

Multi response optimization

Grey relational analysis (GRA)

It was performed on the response values, which aimed to condense the parameters of multiple responses into a single response. Multi response optimization is performed by integrating the Taguchi method and GRA to identify the optimal process parameters (Mishra et al., 2015). In GRA, a multi-response problem is converted to an equivalent single-response problem by calculating a Grey grade. Grey relational analysis is used to combine all performance characteristics to be evaluated into a single value that can be used as a single characteristic in optimization problems (Bangphan et al., 2022).

Grey relational coefficient:

After pre-processing and normalization of the original data, grey relational coefficients (GRC) are calculated for each run of experiment. The Grey relational coefficient is calculated by normalizing all responses between 0 and 1. The Grey grade is obtained by calculating the average of the Grey relational coefficients of the selected response. Initially, the responses are normalized using equation (2) based on the smaller-better criterion and this is called Grey relational generations. Standard test values are compared to normalized values to determine GRC. The highest Grey relational grade was assigned a rank of 1. Consequently, experiment number 16 is identified as the optimal combination of turning parameters for achieving the best results in terms of surface roughness among all 16 experiments conducted. By utilizing Grey relational analysis, the multi-objective optimization problem is transformed into a single equivalent objective function optimization problem. The Taguchi technique is then employed to identify the best combination of process parameters based on the highest Grey relational grade (1).

This calculation allows for the comparative ranking of all 16 experimental input parameters on a unified scale, with a grade output response of experiment number 16 was rank 1 with the result of GRG was 1 indicating the best performance.

Table 5. Grey Relational Grade

Factors	A	B	C	D	Grey grade relational	Grey Rank relational
Trail no	Column					
	1	2	3	4		
1	1	1	1	1	0.361	14
2	1	2	2	2	0.543	9
3	1	3	3	3	0.339	15

Experimental Analysis of Surface Roughness by Optimizing Machining Parameters in Turning of Aluminium Alloy 075-T651 With Avocado Oil-Based Cutting Fluid Using Taguchi Based Grey Relational Analysis

4	1	4	4	4	0.333	16
5	2	1	2	3	0.407	12
6	2	2	1	4	0.382	13
7	2	3	4	1	0.535	10
8	2	4	3	2	0.55	8
9	3	1	3	4	0.51	11
10	3	2	4	3	0.642	6
11	3	3	1	2	0.562	7
12	3	4	2	1	0.692	5
13	4	1	4	2	0.98	2
14	4	2	3	1	0.908	3
15	4	3	2	4	0.785	4
16	4	4	1	3	1	1

Table 6. Response table for mean Grey relational grade (GRG)

Level	Input parameters			
	Avocado oil	Cutting speed	Feed rate	Depth of cut
Level 1	0.394	0.564	0.576	0.624
Level 2	0.468	0.618	0.606	0.658
Level 3	0.601	0.555	0.576	0.597
Level 4	0.918	0.643	0.622	0.502
Max.	0.918	0.643	0.622	0.658
Min.	0.394	0.555	0.576	0.502
Max.- Min.	0.524	0.088	0.046	0.156
Rank	1	3	4	2

In table 6, it was observed that the difference between the maximum and minimum values of GRG (Grey Relational Grade) for the parameter of avocado oil-based cutting fluid is higher compared to cutting speed, feed rate, and depth of cut. The equation in the above states that the larger the Grey relational grade, the better the multiple quality characteristics. The values in the table 6 are highlighted in the bold to indicate the optimal values of the machining parameters. It can be concluded that avocado oil-based cutting fluid has a stronger effect on the performance characteristics compared to the other parameters. The optimized parameters

Experimental Analysis of Surface Roughness by Optimizing Machining Parameters in Turning of Aluminium Alloy 075-T651 With Avocado Oil-Based Cutting Fluid Using Taguchi Based Grey Relational Analysis

are as follows: avocado oil (9%), depth of cut (1.0 mm), cutting speed (1200 rpm), and feed rate (100 mm/min).

Regression Analysis

The obtained data was analysed using multiple regression analysis with Minitab software version 19. The independent variables in the analysis included avocado oil fluid, cutting speed, feed rate, and depth of cut, while the dependent variable of interest was surface roughness. Separate regression models were developed to predict surface roughness based on these cutting variables. The regression equations for the cutting parameters avocado oil, cutting speed, feed rate, and depth of cut were derived from the regression analysis conducted in Minitab.

Regression Analysis: surface roughness versus Oil, Speed, Feed, Doc

Optimum parameters obtained from main effect plots of surface roughness are: Oil (9%), cutting speed (900 rpm), feed rate (95 mm/min) and depth of cut (1.5 mm). Hence;

Regression Equation of surface roughness, Ra:

$$Ra = 7.12 - 0.005CS - 0.1FR - 0.07DoC + 0.788AO$$

$$Ra = 7.12 - 0.005 \times 900 - 0.1 \times 95 - 0.07 \times 1.5 + 0.788 \times 9$$

$$Ra = 0.11$$

Confirmation tests

The confirmation test is conducted to determine whether the predicted results, based on the optimized process parameters, fall within an acceptable range when compared to the experimental results. Thus, analysing the confirmation test results can be concluded that the predicted values surface roughness appear to be in good agreement with the experimental values. Confirmation tests were carried out by utilizing the optimal levels of the provided parameters for all three cases. Specifically, for Surface roughness with avocado oil based cutting fluid, the optimal levels of cutting parameters were avocado oil based cutting fluid at level 4, cutting speed at level 1, feed rate at level 3 and depth of cut at level 3. The experimental value of Ra was found to be 0.12 μm which is very close to 0.11 μm as predicted by equation. The results obtained from the generated equations, as well as the corresponding experimental values and percentage errors, have been calculated and are now presented in table 7 below.

$$\text{Percentage error (\%)} = \frac{\text{Experimental value} - \text{Calculated value}}{\text{Experimental value}} \times 100 \quad \text{Eq. (5)}$$

Table 7. Confirmation test for TWR, MRR and Ra

S/N	Response	Calculated value	Experimental value	Percentage Error (%)
1	Surface roughness (μm)	0.11	0.12	9.09

The confirmation test results presented in table 36, showed that the use of avocado oil based cutting fluid in the milling of Alloy 075-T651 work piece produced percentage errors of 9.09% (surface roughness). In general, these percentage errors are considered statistically acceptable due to their values being below 10%. These results validate that a low percentage error was achieved, thereby indicating a strong correlation between the experimental results and the predicted regression models. In addition, the turning operation conducted using the formulated avocado oil based cutting fluid produced better surface roughness, compared to the other machining operation done using the different types of vegetable oil based cutting fluid. These findings revealed that the formulated avocado oil based cutting fluid can serve as a possible substitute for another vegetable oil based cutting fluid in the turning of machining operation of Alloy 075-T651.

Experimental Analysis of Surface Roughness by Optimizing Machining Parameters in Turning of Aluminium Alloy 075-T651 With Avocado Oil-Based Cutting Fluid Using Taguchi Based Grey Relational Analysis

Conclusion and Recommendation

Conclusion

This study explores the experimental evaluation and optimization of tool wear rate, material removal rate, and surface roughness as responses in turning Alloy 075-T651 with tungsten carbide cutting tool using the Taguchi method. The findings from experimentation of these responses conclusions are drawn in the following:

The surface roughness by using surface roughness tester and Taguchi design of experiment using Minitab software version 19 to make simpler and minimized the needed machining runs in order to succeed the needed optimum result from the responses. The performance of the individual responses on the input parameters were accessed using Taguchi method through the evaluation and optimization of the turning parameters. Conclusions are drawn from the findings obtained through experimentation of these responses, as follows: The evaluation from the orthogonal optimal turning parameters for the surface roughness are 9% of avocado oil based cutting fluid (level 4), cutting speed 820 rpm (level 1), feed rate 132mm/min(level 3) and depth of cut 1.5mm(level 3).

The ANOVA show that the contribution of input parameters of avocado oil fluid, depth of cut, speed and feed rate has significant effect on the surface roughness with avocado oil fluid (11.45%), depth of cut (2.67%), cutting speed (76.78%) and feed rate(2.82%). So, cutting speed (76.78%) are the greatest significant parameters in decreasing of surface roughness. The confirmation tests carried out using regression equations show reliable results as the percentage error was 9.09%, for surface roughness respectively. These percentage errors are generally believed statically acceptable (<10%).

This experimental study shows that avocado oil based cutting fluid could be used in machining process with potential ability to reduce the occupational health risks, lower costs towards waste treatment due to their higher biodegradability and better performance rate. From Taguchi analysis the optimized multi-response turning parameters was achieved by using the parameters are avocado oil (9%), cutting speed (900 rpm), feed rate (95 mm/min) and depth of cut (1.5mm).

Recommendation

Extended studies are needed to evaluate and optimize the formulated avocado oil-based cutting fluid and address different machining process applications such as grinding, drilling and milling of different types of metals with different cutting tool and other machining variables such as cutting force, friction coefficient, cutting temperature, chip formation, which helps the machine industry access an environmentally friendly cutting fluid that produces suitable machined products. Thus, for future work, it is recommended to increase the range of cutting parameters such as cutting speed, feed rate, and depth of cut, with different mixing ratios of water with oil, which can later be used in different machining operation with fluid apply method to compare their effectiveness.

References

- [1] W. Xu, C. Li, J. Singh, and S. S. Gill, "Comparative analysis of cutting fluids Comparative analysis of cutting fluids," 2020, doi: 10.1088/1757-899X/966/1/012095.
- [2] S. M. Agrawal and N. G. Patil, "Experimental study of non edible vegetable oil as a cutting fluid in machining ScienceDirect ScienceDirect ScienceDirect ScienceDirect Experimental study of non edible vegetable oil as a cutting fluid in machining MQL

Experimental Analysis of Surface Roughness by Optimizing Machining Parameters in Turning of Aluminium Alloy 075-T651 With Avocado Oil-Based Cutting Fluid Using Taguchi Based Grey Relational Analysis

- Experimental study of non of edible v,” *Procedia Manuf.*, vol. 20, no. January, pp. 207–212, 2018, doi: 10.1016/j.promfg.2018.02.030.
- [3] P. C. Priarone, M. Robiglio, L. Settineri, and V. Tebaldo, “Effectiveness of minimizing cutting fluid use when turning difficult-to-cut alloys,” *Procedia CIRP*, vol. 29, pp. 341–346, 2015, doi: 10.1016/j.procir.2015.02.006.
- [4] A. J. B. Sutton and D. J. Sapsford, “Physicochemical Characterization of Sludge Originating from Vegetable Oil – Based Cutting Fluids,” pp. 1–8, 2012, doi: 10.1061/(ASCE)EE.1943-7870.0001014.
- [5] S. O. Yakubu and M. Y. Bello, “Evaluation of Neem Seed Oil As a Cutting Fluid in Orthogonal Machining of Aluminum Manganese Alloy (Al-Mn) in Turning Operation,” *Eur. J. Eng. Technol.*, vol. 3, no. 3, pp. 15–24, 2015, [Online]. Available: www.idpublications.org
- [6] C. Harumi *et al.*, “Curcuma Longa L . vegetable oil characterization as cutting fluid base and Curcuma Longa L . essential oil antimicrobial properties analysis for machining application,” 2020.
- [7] C. A. S. Bork, J. F. de S. Gonçalves, J. de O. Gomes, and J. Gheller, “Performance of the jatropha vegetable-base soluble cutting oil as a renewable source in the aluminum alloy 7050-T7451 milling,” *CIRP J. Manuf. Sci. Technol.*, vol. 7, no. 3, pp. 210–221, 2014, doi: 10.1016/j.cirpj.2014.04.004.
- [8] C. H. Yu, R. L. Peng, T. L. Lee, V. Luzin, J. E. Lundgren, and J. Moverare, “Anisotropic behaviours of LPBF Hastelloy X under slow strain rate tensile testing at elevated temperature,” *Mater. Sci. Eng. A*, vol. 844, no. January, p. 143174, 2022, doi: 10.1016/j.msea.2022.143174.
- [9] T. Stapenhurst and A. Bendell, *Taguchi Methods*, vol. 41, no. 9. 1990. doi: 10.2307/2583510.
- [10] D. K. Patel and R. G. Jivani, “Experimental Investigations on Material Removal Rate, Power Consumption and Surface Roughness of EN19 Steels in Turing using Taguchi Method - A Review,” vol. 3, no. 2, pp. 2648–2651, 2014.
- [11] V. Saikumar, V. Venkatesh, and P. Sivaiah, “Multi-Objective Optimization in CNC Milling Process of Al-Cu-Zn Alloy Matrix Composite by Using Taguchi-Grey Relational Analysis Technique,” *Int. J. Adv. Mater. Manuf. Charact.*, vol. 5, no. 1, pp. 661–672, 2015, doi: 10.11127/ijammc.2015.03.05.

Experimental Analysis of Surface Roughness by Optimizing Machining Parameters in Turning of Aluminium Alloy 075-T651 With Avocado Oil-Based Cutting Fluid Using Taguchi Based Grey Relational Analysis

- [12] K. Krishnaiah and P. Shahabudeen, *Applied Experimental Design and Taguchi Method*. 2012.
- [13] H. Demirpolat, R. Binali, A. D. Patange, S. S. Pardeshi, and S. Gnanasekaran, “Comparison of Tool Wear, Surface Roughness, Cutting Forces, Tool Tip Temperature, and Chip Shape during Sustainable Turning of Bearing Steel,” *Materials (Basel)*., vol. 16, no. 12, p. 4408, 2023, doi: 10.3390/ma16124408.
- [14] S. K. Nayak, J. K. Patro, S. Dewangan, and S. Gangopadhyay, “Multi-objective Optimization of Machining Parameters During Dry Turning of AISI 304 Austenitic Stainless Steel Using Grey Relational Analysis,” *Procedia Mater. Sci.*, vol. 6, no. Icmpe, pp. 701–708, 2014, doi: 10.1016/j.mspro.2014.07.086

Supplementary Files

This is a list of supplementary files associated with this preprint. Click to download.

- [AberaAyza1Table.docx](#)
- [AberaAyza1figure.docx](#)